

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-136313

(43)Date of publication of application : 16.05.2000

(51)Int.Cl. C08L101/10
C08L 65/00

(21)Application number : 10-313557

(71)Applicant : ASAHI GLASS CO LTD

(22)Date of filing : 04.11.1998

(72)Inventor : DOI TAKAO
WATABE TAKASHI
ONOGUCHI TATSUO
HAYASHI TOMOYOSHI

(54) ROOM-TEMPERATURE-VULCANIZABLE COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a vulcanizable composition having very rapid surface curability and developing surface weather resistance by using a polymer having specified hydrolyzable silicon groups, an air-curable compound and/or photocurable compound as the essential components.

SOLUTION: This composition is a room-temperature-vulcanizable one consisting essentially of a polymer having hydrolyzable groups of the formula, said polymer at least partially consisting of a polymer having hydrolyzable groups of the formula (wherein a is 3), and an air-curable compound and/or a photo-curable compound. In the formula, R1 is a 1-20C monovalent organic group; X is OH or a hydrolyzable group. The air-curable compound used is desirably a compound having an unsaturation undergoing polymerization under the influence of atmospheric oxygen and is desirably a liquid diene polymer, an oil from modification thereof, or the like. The photocurable compound is typified by an unsaturated acrylic compound, polyvinyl cinnamate, an azided resin, and the like, among which the unsaturated acrylic compound is particularly desirable.



* NOTICES *


JPO and INPI are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.*** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1]It is a polymer which has a hydrolytic silicon group expressed with a following formula (1). A room-temperature-curing nature constituent in which some or all of this polymer uses as an essential ingredient a polymer (A), a curing-in-air compound (K), and/or a photorealist compound (L) which are the polymers which have a hydrolytic silicon group which is 3 in a of a formula (1).



(R¹ shows a univalent organic group substitution of the carbon numbers 1-20, or unsubstituted among a formula (1), X shows a hydroxyl group or a hydrolytic basis, and a shows 1, 2, or 3.) however, when those R¹ may be the same, or may differ, when two or more R¹ exist, and two or more X exists, those X may be the same or may differ.

[Claim 2]The room-temperature-curing nature constituent according to claim 1 whose molecular weights of a polymer (A) are 8000-50000.

[Claim 3]The room-temperature-curing nature constituent according to claim 1 or 2 which is a

polyoxyalkylene polymer (B) in which a polymer (A) has a hydrolytic silicon group expressed with a formula (1).

[Claim 4]The room-temperature-curing nature constituent according to claim 3 whose molecular-weight-distribution M_w/M_n of a polyoxyalkylene polymer (B) is 1.7 or less.

[Claim 5]A polyoxyalkylene polymer (B) at the end of a polyoxyalkylene polymer produced under existence of an initiator by polymerizing cyclic ether by making a composite metal cyanide complex into a catalyst. The room-temperature-curing nature constituent according to claim 3, 4, 5, or 6 in which a polymer produced by introducing a hydrolytic silicon group expressed with a formula (1).

[Claim 6]. A polyoxyalkylene polymer (B) is obtained by polymerizing cyclic ether under existence of an initiator. The room-temperature-curing nature constituent according to claim 3, 4, or 5 which is a polymer produced by molecular-weight-distribution M_w/M_n introducing a hydrolytic silicon group expressed with a formula (1) into an end of a polyoxyalkylene polymer which is 1.7 or less.

[Claim 7]The room-temperature-curing nature constituent according to claim 3, 4, 5, or 6 in which a polyoxyalkylene polymer (B) contains a polymer (D) further produced by polymerizing a polymerization nature unsaturation group content monomer (C).

[Claim 8]The room-temperature-curing nature constituent according to claim 3, 4, 5, or 6 in which a polyoxyalkylene polymer (B) contains a polymer (D) further produced by polymerizing a polymerization nature unsaturation group content monomer (C) in a polyoxyalkylene polymer (B).

[Claim 9]The room-temperature-curing nature constituent according to claim 7 or 8 which is a monomer which has a hydrolytic silicon group which a part or all of a polymerization nature unsaturation group content monomer (C) has a polymerization nature unsaturation group, and is expressed with a glycidyl group and/or a formula (1).

[Claim 10]Claims 1, 2, 3 and 5 which are the polymers in which some or all of a polymer (A) has simultaneously a hydrolytic silicon group whose a in a hydrolytic silicon group whose a in a formula (1) is 1 or 2, and a formula (1) is 3, a room-temperature-curing nature constituent given in 6, 7, 8, or 9.

[Claim 11]Claims 1, 2, 3 and 5 in which a polymer (A) contains both polymers which has a hydrolytic silicon group whose a in a polymer in which a in a formula (1) has a hydrolytic silicon group which is 1 or 2, and a formula (1) is 3, a room-temperature-curing nature constituent given in 6, 7, 8, or 9.

[Claim 12]Claims 1, 2, 3 and 5 whose polymer (A) is a polymer which has only a hydrolytic silicon group whose a in a formula (1) is 3 as a hydrolytic silicon group, a room-temperature-curing nature constituent

[Translation done.]

* NOTICES *

JPO and INPII are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.*** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention]This invention relates to the hardenability constituent hardened under hygroscopic-surface-moisture existence.

[0002]

[Description of the Prior Art]The polyoxyalkylene polymer which has a hydrolytic silicon group at the end employs efficiently the feature that a hardened material has rubber elasticity, and is used for the use of a coating composition, a seal constituent, etc.

[0003]

[Problem to be solved by the invention]The method of making an end harden various kinds of polymers which have a hydrolytic silicon group, and using it for sealant, adhesives, etc. is known well, and is a useful method industrially. The polymer especially whose main chain is polyoxyalkylene among such polymers is liquefied at a room temperature, and when a hardened material holds pliability also at low temperature comparatively and uses for sealant, adhesives, etc., it is provided with the desirable characteristic.

[0004] As a polymer of such hygroscopic-surface-moisture hardenability, are indicated to JP,61-18582,B, JP,3-72527,A, or JP,3-47825,A. The polymer which has a hydrolytic silicon group which is a polymer which has a hydrolytic silicon group at the end, and two hydrolytic bases per silicon atom combine in order to hold elongation and pliability, it is the polymer which is indicated to JP,58-10418,B and JP,58-10430,B and which has a hydrolytic silicon group which three hydrolytic bases per silicon atom combine — a molecular weight — 6000 or less — the polymer of low molecular weight is known comparatively.

[0005]However, when such a polymer is used at a use etc. and low temperature of adhesives etc., To take [when you need a very quick cure rate especially, the cure rate is not enough, and] out pliability after hardening. Crosslinking density needed to be reduced, therefore since crosslinking density was not enough, there was stickiness (surface tackiness), and there was a problem that a crack went into the surface easily in the long run by weathering degradation. In order to solve this problem, A photoresist compound and a curing-in-air compound. A method of adding JP,62-26349,B. It is tried by JP,1-198661,A, JP,2-117954,A, JP,3-160053,A, JP,5-70531,A, JP,5-65400,A, JP,5-65407,A, JP,7-196909,A, JP,8-269315,A, etc., An example which uses a narrow polymer of molecular weight distribution especially for JP,5-65400,A and JP,5-65407,A is indicated. However, these publicly known examples were substantially difficult to only know an example in a monoalkyl dialkoxo silyl group as a hardenability functional group, and to make a cure rate quick in such a case.

[0006]As mentioned above, a presentation which can improve the very quick hardening characteristic and surface weatherability without worsening the pliability and workability greatly was desired to a polymer which has a hydrolytic silicon group.

[0007]

[Means for solving problem]This invention is the following invention about the room-temperature-curing nature constituent which was extremely excellent in the hardening characteristic and surface weatherability by using a specific curing-in-air compound and a photoresist compound.

[0008]It is a polymer which has a hydrolytic silicon group expressed with a following formula (1). The room-temperature-curing nature constituent in which some or all of this polymer uses as an essential ingredient the polymer (A), curing-in-air compound (K), and/or photoresist compound (L) which are the polymers which have a hydrolytic silicon group which is 3 in a of a formula (1).

[0009]— SIX R¹_{3-a} ... (1)

(R¹ shows a univalent organic group the substitution of the carbon numbers 1-20, or unsubstituted among a

formula (1), X shows a hydroxyl group or a hydrolytic basis, and a shows 1, 2, or 3,) however, when those R¹ may be the same, or may differ, when two or more R¹ exist, and two or more X exists, those X may be the same or may differ.

[0010](Polymer (A)) In this invention, although polyoxyalkylene, polyester, polycarbonate, polyolefine, etc. are mentioned as a main chain of a polymer (A), especially the thing that a main chain consists of polyoxyalkylene intrinsically is preferred. Hereafter, a main chain represents and explains the polymer (henceforth a polyoxyalkylene polymer (B)) which is polyoxyalkylene among polymers (A).

[0011](Polyoxyalkylene polymer (B)) A polyoxyalkylene polymer (B) which has a hydrolytic silicon group expressed with a formula (1) is proposed by JP,3-47825,A, JP,3-72527,A, JP,3-79627,A, etc., for example. As for a polyoxyalkylene polymer (B), it is preferred to use as a raw material a polyoxyalkylene polymer which has a functional group, to make it not pass to the end via an organic group, to introduce a hydrolytic silicon group and to be manufactured so that it may state below.

[0012]As a raw material polyoxyalkylene polymer, a thing of a hydroxyl group end which makes cyclic ether etc. react and is manufactured is preferred under existence of a catalyst and existence of an initiator. As an initiator, a hydroxy compound etc. which have one or more hydroxyl groups can be used. As cyclic ether, ethylene oxide, propylene oxide, butylene oxide, hexyleneoxide, a tetrahydrofuran, etc. are mentioned. As a catalyst, alkaline metal catalysts, such as a potassium system compound and a caesium system compound, a composite metal cyanide complex catalyst, a metalloporphyrin catalyst, etc. are mentioned.

[0013]In this invention, it is preferred to use a polyoxyalkylene polymer of the amount of polymers of the molecular weights 8000-50000 as a raw material polyoxyalkylene polymer. Therefore, by [which manufactured using an alkali catalyst etc.] making many halogenated compounds, such as a methylene chloride, react to a polyoxyalkylene polymer of low molecular weight comparatively. It is preferred to use a polyoxyalkylene polymer manufactured using a polyoxyalkylene polymer and a composite metal cyanide complex catalyst which are acquired by quantifying many.

[0014]Moreover — especially — the ratio of weight average molecular weight (M_w) and a number average molecular weight (M_n) — it being preferred that M_w/M_n uses 1.7 or less polyoxyalkylene polymer, and. As for M_w/M_n , it is still more preferred that it is 1.6 or less, and, as for M_w/M_n , it is preferred that it is especially 1.5 or less.

[0015]The polyoxyalkylene polymer (B) which has a hydrolytic silicon group of this invention is obtained by denaturalizing and using an end group as a hydrolytic silicon group further, by using such a polyoxyalkylene polymer as a raw material. When the polyoxyalkylene polymer (B) obtained considering it as a raw material is stiffened so that M_w/M_n of a raw material polyoxyalkylene polymer is small, the elongation of a hardened material serves as high intensity greatly, and the viscosity of a polymer becomes low, and what has a the same elastic modulus is excellent in workability. Especially in such a polyoxyalkylene polymer, make a composite metal cyanide complex into a catalyst, and Under existence of an initiator, Especially the thing produced by polymerizing alkylene oxide is preferred, and what denaturalized and used the end of such an alkylene oxide polymer as the hydrolytic silicon group is the most preferred.


[0016]The complex which uses zinc hexa cyanocobaltate as the main ingredients as a composite metal cyanide complex is preferred, and ether and/or an alcoholic complex are especially preferred. The presentation can use what is intrinsically indicated to JP,46-27250,B. In this case, as ether, ethyleneglycol dimethyl ether (glyme), diethylene glycol dimethyl ether (jig lime), etc. are preferred, and especially glyme is preferred from a point of the handling at the time of manufacture of a complex. As alcohol, t-butanol is preferred.

[0017]As for the functional group number of a raw material polyoxyalkylene polymer, two or more are preferred. As for especially the functional group number of a raw material polyoxyalkylene polymer, 2 or 3 is preferred to enlarge pliability as the hardened material characteristic. As for especially the functional group number of a raw material polyoxyalkylene polymer, when acquiring a good adhesive property and hardenability, 3-8 are preferred.

[0018]As a raw material polyoxyalkylene polymer, the copolymer of a polyoxyethylene, polyoxypropylene, polyoxy butylene, polyoxy hexylene, polyoxy tetramethylen, and two or more sorts of cyclic ether is specifically mentioned.


[0019]Especially a desirable raw material polyoxyalkylene polymer is a polyoxypropylene polyol of 2 - 6 value, and are polyoxypropylene diol and polyoxypropylene triol especially. When using for the method of the following (b) or (**), the polyoxyalkylene polymer of olefin ends, such as an allyl end polyoxypropylene monooar, can also be used.

[0020] This polyoxoalkylene polymer (B) has a hydrolytic silicon group expressed with the end or side chain of a chain with a following formula (1).



(R^1 , R^2 , X, and a are the same as the above among a formula (5).) An active hydrogen containing group as formula (1), X is a hydroxyl group or a hydrolytic basis, and a is 1, 2, or 3.) However, when two or more R^1 exist, those R^1 may be the same, or may differ, and when two or more X exists, those X may be the same or may differ.

[0021] The hydrolytic silicon group expressed with a formula (1) is usually introduced into a raw material polyoxoalkylene polymer via an organic group. That is, as for a polyoxoalkylene polymer (B), it is preferred to have a basis expressed with a formula (2).



(A divalent organic group, R^1 , X, and a of R^0 are the same as that of the above among a formula (2).)

[0022] R^1 in formula (1) (2) is a univalent organic group substitution of the carbon numbers 1-20, or unsubstituted. It is a with a carbon number of eight or less alkyl group, a phenyl group, or a fluoro alkyl group preferably, and they are a methyl group, an ethyl group, a propyl group, a butyl group, a hexyl group, a cyclohexyl group, a phenyl group, etc. especially preferably, when two or more R^1 exist, those R^1 may be the same, or may differ.


[0023] As a hydrolytic basis in X, a halogen atom, an alkoxy group, an acyloxy group, an alkenyloxy group, a carbamoyl group, an amino group, an aminoxy group, a KETOKISHI mate group, etc. are mentioned, for example.

[0024] As for a carbon number of a hydrolytic basis which has a carbon atom among these, six or less are preferred, and four especially or less are preferred. As desirable X, a with a carbon number of four or less alkoxy group, an alkenyloxy group especially a methoxy group, an ethoxy basis, a propoxy group, or a propenyloxy group can be illustrated, when two or more X exists, those X may be the same or may differ.

[0025] a is 1, 2, or 3. As for the number of the hydrolytic silicon groups in one molecule of polymers, 1-8 are preferred, and 2-especially 6 are preferred.

[0026] Although the method in particular of introducing a hydrolytic silicon group to a raw material polyoxoalkylene polymer is not limited, it can be introduced, for example by (b) of the following - the method of (**).

[0027] (**) A method to which the hydrosilyl compound expressed with it by a formula (3) after introducing an olefin group into the end of the polyoxoalkylene polymer which has a hydroxyl group is made to react.




(R^1 , X, and a are the same as the above among a formula (3).)

[0028] The method of making the compound which has an unsaturation group and a functional group react to the terminal hydroxyl groups of the polyoxoalkylene polymer which has a hydroxyl group, and combining it by the ether bond, the ester bond, a urethane bond, or carbonate combination as a method of introducing an olefin group, is mentioned. When polymerizing alkylene oxide, the method of introducing an olefin group into the side chain of a raw material polyoxoalkylene polymer can also be used by adding and carrying out copolymerization of the olefin group content epoxy compounds, such as allyl glycidyl ether.

[0029] When making a hydrosilyl compound react, catalysts, such as a platinum system catalyst, a rhodium system catalyst, a cobalt system catalyst, a palladium system catalyst, and a nickel series catalyst, can be used. Platinum system catalysts, such as chloroplatinic acid, platinum metal, a platinum chloride, and a platinum olefin complex, are preferred. As for the reaction to which a hydrosilyl compound is made to react, it is preferably preferred to carry out at the temperature of 60-120 °C for several hours 30-150 °C.

[0030] (**) A method to which a compound expressed with an end of a polyoxoalkylene polymer which has a hydroxyl group by a formula (4) is made to react.




(R^1 , X, and a are the same as the above among a formula (4).) R^2 is a divalent hydrocarbon group of the carbon numbers 1-17. A publicly known urethane-ized catalyst may be used in the case of the above-mentioned reaction. As for the above-mentioned reaction, it is preferably preferred to carry out at temperature of 50-150 °C for several hours 20-200 °C.

[0031] (**) A method to which W basis of a silicon compound expressed with a formula (5) to this isocyanate group is made to react after making polyisocyanate compounds, such as tolylene diisocyanate, react to an

http://www4.ipdl.inpit.go.jp/cgi-bin/tran_web.cgi_ejic?atw_u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/18

end of a polyoxoalkylene polymer which has a hydroxyl group and considering it as an isocyanate group end.



(R^1 , R^2 , X, and a are the same as the above among a formula (5).) An active hydrogen containing group as which W is chosen from a hydroxyl group, a carboxyl group, a sulfinyl group, and an amino group (the 1st class or the 2nd class).

[0032] (**) A method to which the olefin group and a sulfinyl group of a silicon compound expressed with a formula (5) whose W is a sulfinyl group are made to react after introducing an olefin group into an end of a polyoxoalkylene polymer which has a hydroxyl group.

[0033] W as a silicon compound expressed with the formula (5) which is a sulfinyl group, 3-mercaptopropyltrimethoxysilane, 3-mercaptopropylmethyl dimethoxysilane, 3-mercaptopropylmethyl methoxysilane, 3-mercaptopropyl triethoxysilane, etc. are mentioned.

[0034] Polymerization initiators, such as a radical generator, may be used, and it may be made to react with radiation or heat in the case of the above-mentioned reaction, without using a polymerization initiator depending on the case. As a polymerization initiator, a polymerization initiator, a metal compound catalyst, etc. of a peroxide system, azo, or a redox system are mentioned, for example. Specifically as a polymerization initiator, 2,2'-azobisisobutyronitrile, 2,2'-azobis 2-methylbutyronitrile, benzoyl peroxide, t-alkyl peroxy ester, acetyl peroxide, diisopropyl peroxy carbonate, etc. are mentioned. As for the above-mentioned reaction, it is preferably preferred to carry out at 50-150 °C for several hours - tens hours 20-200 °C.

[0035] (When a main chain is except a polyoxoalkylene polymer) When the main chains of a polymer (A) are polyester and polycarbonate, it can manufacture by the same process as a polyoxoalkylene polymer (B) by using polyester of a hydroxyl group end, and polycarbonate of a hydroxyl group end as a raw material, respectively.

[0036] When a main chain is polyolefine, it can manufacture by the same process as a polyoxoalkylene polymer (B) by using polyolefine of hydroxyl group ends, such as a polybutadiene polyol and a hydrogenation polybutadiene polyol, as a raw material. After having used 1,4-bis(1-chloro-1-methylethyl)benzene as the initiator, making boron trichloride into the catalyst and polymerizing isobutylene, it can manufacture by the same process as a polyoxoalkylene polymer (B) by using the manufactured isobutylene system polymer which carried out the dehydrochlorination reaction and which has an isopropenyl group at the end as a raw material.

[0037] (Hydrolytic silicon group whose a in a formula (1) is 3) It requires that the polymer (A) in this invention is a polymer in which all have "a hydrolytic silicon group whose a in a formula (1) is 3" (henceforth "a hydrolytic silicon group (E)") in part.

[0038] As "a hydrolytic silicon group (E)", especially the basis whose X in a formula (1) is a with a carbon number of four or less alkoxy group, i.e., the bird alkoxy silyl groups which has a with a carbon number of four or less alkoxy group, is preferred. The polymer which has bird alkoxy silyl groups has dramatically high reactivity, and especially its early cure rate is dramatically quick.

[0039] Usually, in the hydrolysis reaction in the hydrolytic silicon group expressed with a formula (1), A silanol group is generated by a reaction with water (silanol group generating reaction expressed with -SiX+H₂O->-SiOH+HX). It is thought that it progresses by the reaction (condensation reaction) for which the silanol groups furthermore produced condense condensation or a silanol group, and a hydrolytic silicon group, and they produce a siloxane bond. Once a silanol group occurs, it is thought that a condensation reaction goes smoothly. Bird alkoxy silyl groups has the very quick reaction velocity in the early stages of a silanol group generating reaction as compared with an alkyl dialkoxysilyl group or dialkyl alkoxy silyl groups. Therefore, it is thought that it has the effect that the hardenability constituent of this invention has short time until it reveals strength property sufficient in a short time and results especially in an adhesive manifestation.

[0040] A direction of bird alkoxy silyl groups which has an alkoxy group with a carbon number small among bird alkoxy silyl groups. Since reaction velocity in early stages of a silanol group generating reaction is quicker than bird alkoxy silyl groups which has an alkoxy group with a large carbon number, it is desirable, A trimethoxysilyl group and a triethoxysilyl group are more preferred, and since reaction velocity [in / in a trimethoxysilyl group / early stages of a silanol group generating reaction] is very quick, it is the most desirable. Therefore, it is most preferred that it is a trimethoxysilyl group as "a hydrolytic silicon group (E)." A rate of a hydrolytic silicon group (E) in a hydrolytic silicon group expressed with a formula (1) in a polymer (A) can be changed according to a use, the characteristic to need, etc.

http://www4.ipdl.inpit.go.jp/cgi-bin/tran_web.cgi_ejic?atw_u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/18

[0041]When a polymer (A) is a polymer which has a hydrolytic silicon group (E) as this hydrolytic silicon group, That is, when about 100% of hydrolytic silicon groups (namely, 80 to 100%) expressed with a formula (1) in a polymer (A) are hydrolytic silicon groups (E), it is effective in a cure rate being large, and a room-temperature-curing nature constituent excellent in especially hardenability that results in an adhesive manifestation is obtained. In this case, it is preferred that 95 to 100% is a hydrolytic silicon group (E) especially 90 to 100% of a hydrolytic silicon group (E) expressed with a formula (1).

[0042]When a hydrolytic silicon group and a hydrolytic silicon group (E) whose a in a formula (1) is 1 or 2 are intermingled, a room-temperature-curing nature constituent which may be compatible in a good extension characteristic and fast curability is obtained.

[0043]In this case, it is preferred that the percentage of a hydrolytic silicon group (E) in all the hydrolytic silicon groups expressed with a formula (1) in a polymer (A) is 5 to 80%. The characteristic according to a demand is freely controllable by changing this rate arbitrarily. That is, when the percentage of a hydrolytic silicon group (E) is 5 to 50%, while raising hardenability, a good extension characteristic and pliability which are needed by sealant etc. can be provided. When the percentage of a hydrolytic silicon group (E) is 50 to 80%, an extension characteristic needed for elastic adhesives etc. can fully be secured, and hardenability can be improved by leaps and bounds.

[0044]As for hydrolytic silicon groups other than a hydrolytic silicon group (E), in a hydrolytic silicon group expressed with a formula (1), it is preferred that a in a formula (1) is especially a hydrolytic silicon group of 2. It is preferred that it is especially a dialkoxyl alkyl silyl group which has a with a carbon number of four or less alkoxy group. A dimethoxymethyl silyl group is the most preferred.

[0045]There are following method (**) and (**) in the method of obtaining a polymer (A) that the hydrolytic silicon group which is 1 or 2, and the hydrolytic silicon group (E) were intermingled, for example, and a in a formula (1) may use the method of (**) and (**) together.

(**) As a polymer (A), a in a formula (1) uses the polymer which has simultaneously the hydrolytic silicon group and hydrolytic silicon group (E) which are 1 or 2.


(**) As a polymer (A), a in a formula (1) uses both polymers (A) which has the polyoxyalkylene polymer (B) and hydrolytic silicon group (E) which have a hydrolytic silicon group which is 1 or 2.

[0046]As for the molecular weight of a polymer (A), although the molecular weight of the polymer (A) in this invention can choose a suitable value according to the use used, it is preferred that it is 8000-50000.

[0047]For uses, such as sealant than to which greater importance is attached to pliability, the polymer of the molecular weights 8000-50000 is preferred. As for a molecular weight, it is preferred that it is especially 8000-25000, and it is most preferred that it is 12000-20000. For the use of the adhesives etc. with which intensity is demanded, the polymer of the molecular weights 8000-30000 is preferred. When becoming what has a hardened material weak when lower than 8000 and exceeding 30000, workability gets remarkably bad for hyperviscosity. As for a molecular weight, it is more preferred that it is 8000-20000, and it is preferred that it is especially 12000-20000.

[0048](Polymer (D) produced by polymerizing a polymerization nature unsaturation group content monomer (C)) A room-temperature-curing nature constituent which uses a polymer (A) as an essential ingredient is excellent in hardenability. In this invention, when using a polyoxyalkylene polymer (B) among polymers (A), it is preferred that a polyoxyalkylene polymer (B) contains a polymer (D) produced by polymerizing a polymerization nature unsaturation group content monomer (C) further. By containing a polymer (D), an effect of adhesive grant in an initial stage of a hardening reaction, i.e., an effect that time until it reveals bond strength becomes very short, is acquired.

[0049]Although a compound shown, for example with a following formula (6) is mentioned as a typical thing of a polymerization nature unsaturation group content monomer (C), it is not limited to these.



(R, R², R⁴, and R⁵ are a hydrogen atom, a halogen atom, or a univalent organic group independently among a formula, respectively.)


[0050]It is preferred that it is univalent substitution or an unsubstituted hydrocarbon group of the carbon numbers 1-10 as an organic group in R and R⁵. As for R and R⁵, it is more preferred respectively that it is a hydrogen atom. An organic group in R² and R⁴ Univalent substitution or an unsubstituted hydrocarbon group of the carbon numbers 1-10, it is preferred that they are an alkoxy group, a carboxyl group, an alkoxy-carbonyl group, a cyano group, a cyano group content group, an alkenyl group, an acyloxy group, a carbamoyl group, a pyridyl group, a glycidyl group, or a glycidyl group carbonyl group. As for R³, it is preferred that it is especially univalent substitution or an unsubstituted hydrocarbon group of a hydrogen

atom, a halogen atom, or the carbon numbers 1-10.

[0051]As an example of a polymerization nature unsaturation group content monomer (C), Styrene monomers, such as styrene, alpha-methylstyrene, and chlorostyrene; Acrylic acid, Methacrylic acid, methyl acrylate, methyl methacrylate, ethyl acrylate, Ethyl methacrylate, butyl acrylate, butyl methacrylate, 2-ethylhexyl acrylate, Acrylic acid, such as 2-ethylhexyl methacrylate, acrylic acid benzyl, and benzyl methacrylate, Acrylic monomers, such as methacrylic acid or its ester, acrylamide, and methacrylamide; Acrylonitrile, Cyano group content monomers, such as 2,4-dioxyano butene-1; Vinyl acetate, Vinyl ester system monomers, such as vinyl propionate; Butadiene, isoprene, Diene system monomers, such as chloroprene; Vinyl glycidyl ether, allyl glycidyl ether, Glycidyl group content monomer [such as methallyl glycidyl ether, glycidyl acrylate, and glycidyl methacrylate, i, and olefins other than these, unsaturation ester species, a halogenation olefin, vinyl ether, etc. are mentioned.

[0052]A polymerization nature unsaturation group content monomer (C) may use only one sort, and may use two or more sorts together. When a cyano group content monomer, a glycidyl group content monomer, or a styrene monomer is used and acrylonitrile, glycidyl acrylate, glycidyl methacrylate, or styrene is used especially, since a further outstanding adhesive property and a mechanical physical property may be revealed, it is desirable. When requiring rubber elasticity especially after hardening, it is preferred to use acrylic ester.

[0053]The polymerization nature monomer which has a hydrolytic silicon group expressed with a formula (1) can be used as a polymerization nature unsaturation group content monomer (C). The compound expressed with a following formula (7) especially as a polymerization nature monomer which has such a hydrolytic silicon group is preferred.



(R⁷ is a univalent organic group which has a polymerization nature unsaturation group among a formula (7).

R⁶ is a univalent organic group the substitution of the carbon numbers 1-20, or unsubstituted, Y is a hydroxyl group or a hydrolytic basis, and b is 1, 2, or 3.) however, when two or more R⁶ exist, those R⁶ may be the same, or may differ, and when two or more Y exists, those Y may be the same or may differ.

[0054]As a polymerization nature monomer which has a hydrolytic silicon group, the vinyl monomer which has a hydrolytic silicon group, the acrylic monomer which has a hydrolytic silicon group, etc. are mentioned. The following are specifically mentioned and 3-acryloyloxypropyl trimethoxysilane and especially 3-methacryloyl oxypropyl trimethoxysilane are preferred.

[0055]Vinylmethyldimethoxysilane, vinylmethyldiethoxysilane, vinyl methylidyl chlorosilane,

vinyltrimethoxysilane, vinyltriethoxysilane, vinyl trichlorosilane, Vinylsilane, such as tris (2-methoxyethoxy)

vinylsilane. 3-acryloyloxypropylmethyldimethoxysilane, 3-methacryloyl oxypropyl methyl dimethoxysilane, 3-acryloyloxypropyl trimethoxysilane, 3-acryloyloxypropyl triethoxysilane, Acryloyloxy silanes, such as 3-methacryloyl oxypropyl trimethoxysilane and 3-methacryloyl oxypropyl triethoxysilane, and methacryloyloxy silanes

[0056]A compound which has simultaneously a silicon atom which is a polysiloxane compound which has 2-30 silicon atoms other than these, for example, and was combined with a carbon-carbon double bond and a hydrolytic basis can also be used as a polymerization nature monomer which has a hydrolytic silicon group.

[0057]A polymerization nature monomer which has the above-mentioned hydrolytic silicon group may use only one sort, and may use two or more sorts together. When using a polymerization nature monomer which has a hydrolytic silicon group, this monomer has that preferred of *** for 0.01 - 20 weight sections among polymerization nature unsaturation group content monomer (C) 100 weight section.

[0058]As for a part or all of a polymerization nature unsaturation group content monomer (C), it is preferred that it is a monomer which has a hydrolytic silicon group which has a polymerization nature unsaturation group and is expressed with a glycidyl group and/or a formula (1).

[0059](Polymer composition) When a polyoxyalkylene polymer (B) contains a polymer (D) further, a polymer composition which consists of a polyoxyalkylene polymer (B) and a polymer (D) can be manufactured by a method of (**) shown below - (**).

[0060](**) How to mix a polymer (D) produced by polymerizing a polymerization nature unsaturation group content monomer (C) beforehand with a polyoxyalkylene polymer (B).

(**) How to polymerize a polymerization nature unsaturation group content monomer (C) in a polyoxyalkylene polymer (B).

(**) How to change an unsaturation group in a polymer (F) which remains into a hydrolytic silicon group expressed with a formula (1) after polymerizing a polymerization nature unsaturation group content monomer

(C) in a polyoxyalkylene polymer (F) containing an unsaturation group. A converting method of a method to which a hydrosilyl compound expressed with an unsaturation group by a formula (3) is made to react is preferred.

(**) How to change a precursor into a polyoxyalkylene polymer (B) after polymerizing a polymerization nature unsaturation group content monomer (C) in a precursor of a polyoxyalkylene polymer (B).

(**) How to mix with a polyoxyalkylene polymer (B), rank second if needed, and distill off a solvent or a diluent after polymerizing a polymerization nature unsaturation group content monomer (C) under existence of a solvent or a diluent.

[0061]A solvent can be suitably chosen according to the kind of polymerization nature unsaturation group content monomer (C). As a diluent, an unsaturation group content polyoxyalkylene polymer (F) is preferred. The polyoxyalkylene polymer (F) containing an unsaturation group can also be made to exist in a solvent or a diluent in the case of a polymerization.

[0062]Polymerization initiators, such as a radical generator, may be used, and it may be made to polymerize with radiation or heat in the case of a polymerization nature unsaturation group content monomer (C) polymerization, without using a polymerization initiator depending on the case. About a polymerization initiator, polymerization temperature, and polymerization time, it is the same as said (**) described.

[0063]When using a polymer (D) in this invention, it is preferred that the polyoxyalkylene polymer (B) / polymer (D) is used in the range used as $100 / 1 - 1 / 300$ at a weight ratio. It is preferred to be used in $100 / 1 - 1 / 100$, further $100 / 1 - 1 / 10$ especially in respect of workability etc.

[0064]It may be distributing uniformly in the shape of a particle in a polyoxyalkylene polymer (B), or the polymer (D) may be dissolving uniformly again. When the viscosity and the workability of a constituent are taken into consideration, it is preferred to distribute uniformly in the shape of a particle.

[0065]In this invention, a curing-in-air compound (K) and/or a photoresist compound (L) are used with a polymer (A). Use of a curing-in-air compound (K) has an effect in improvement of an initial tack, and use of a photoresist compound (L) has an effect in improvement of resistance to contamination or crack control. A curing-in-air compound (K) and a photoresist compound (L) have especially a preferred thing used together.

[0066]A compound which has in intramolecular an unsaturation group which causes a polymerization by oxygen in the air as a curing-in-air compound (K) used for this invention is preferred. Specifically, a denaturation oil of a denaturation thing of drying oil and drying oil, a liquefied diene system polymer, or a liquefied diene system polymer is preferred.

[0067]As drying oil, tung oil, linseed oil, perilla oil, soybean oil, sunflower seed oil, hempseed oil, etc. are mentioned. Various alkyd resins produced by denaturalizing drying oil as a denaturation thing of drying oil, A resultant of drying oil and functionality polyoxyalkylene, a resultant (urethane oil) of drying oil and an isocyanate compound, an acrylic polymer that denaturalized with drying oil, an epoxy resin which denaturalized with drying oil, and silicon resin which denaturalized with drying oil are mentioned.

[0068]As a liquefied diene system polymer and its denaturation thing, Diene series of the carbon numbers 4-8, such as butadiene, chloroprene, isoprene, and 1,3-pentadiene, homopolymerization or a liquefied polymer produced by making carry out copolymerization, Polymers, such as NBR, SBR, etc. which are produced by making carry out copolymerization of the monomers which have diene series and copolymeric, such as acrylonitrile and styrene, so that diene series may serve as a subject, and those various denaturation things (a malleinized denaturation thing, a boiled oil denaturation thing, etc.) are mentioned.

[0069]Among these, the denaturation thing of drying oil, a liquefied diene system polymer, and a liquefied diene system polymer is preferred. Especially drying oil is preferred. A curing-in-air compound (K) may be used by an one-sort independent, and may use two or more sorts together.

[0070]Concomitant use of the catalyst and metal drier which promote an oxidation hardening reaction with a curing-in-air compound (K) may lighten an effect. As these catalysts and metal driers, metal salt, such as cobalt naphthenate, lead naphthenate, a naphthenic acid zirconium, 2-ethylhexanoic acid cobalt, and 2-ethylhexanoic acid zirconium, an amine compound, etc. are mentioned.

[0071]The amount of [in the case used of using a curing-in-air compound (K)] has 0.01 - 20 preferred weight section to a total of 100 weight sections of a polymer (A) or a polymer (A) and a polymer (D). If the amount used is less than 0.01 weight sections, the improvement effect of the initial tack which is the purpose of using a curing-in-air compound (K) is insufficient, and if 20 weight sections are exceeded, the elongation of a hardened material, etc. will be spoiled. The desirable amount used is one to 10 weight section.

[0072]By operation of light, considerably, molecular structure causes a chemical change for a short time, and the photoresist compound (L) used for this invention produces physical-properties change of hardening etc. for it. As this kind of a compound, many things, such as a constituent containing a monomer, oligomer,

http://www4.ipdl.inpit.go.jp/cgi-bin/tran_web_cgi_ejje?atw_u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/18

resin, or them, are known, and the arbitrary things marketed can be used. An unsaturation acrylic compound, polyvinamic acid vinyl, or azide-sized resin is typical, and especially an unsaturation acrylic compound is preferred.

[0073]As an unsaturation acrylic compound — an acrylyl group or a methacryloyl group — 1- the monomers and oligomer which it has partly, or those mixtures are preferred, and the compound which has especially an acrylyl group is preferred. With a molecular weight of 10000 or less produced by more specifically polymerizing monomers and these monomers, such as di(meth)acrylate of polyhydric alcohol, oligoesters is preferred (acrylate shows acrylate and methacrylate.). (meta) It is below the same. As an example of di(meth)acrylate of polyhydric alcohol, Propyleneglycol di(meth) acrylate, butylene glycol di(meth)acrylate, ethylene glycol di(meth)acrylate, neopentyl glycol di(meth)acrylate, trimethylolpropane bird (meta) acrylate, etc. are mentioned.

[0074]The amount of [in the case used of using a photoresist compound (L)] has 0.01 - 20 preferred weight section to a total of 100 weight sections of a polymer (A) or a polymer (A) and a polymer (D). If the amount used is less than 0.01 weight sections, the contamination-resistant improvement which is the purpose of using a photoresist compound (L) is insufficient, and if 20 weight sections are exceeded, the elongation of a hardened material, etc. will be spoiled. The desirable amount used is one to 10 weight section.

[0075](Room-temperature-curing nature constituent) The following additive agent can also be included by room-temperature-curing nature constituent of this invention. Hereafter, an additive agent is explained.

[0076](Bulking agent) A publicly known bulking agent can be used as a bulking agent. Especially the amount of bulking agent used has 50 - 250 preferred weight section 0.001 to 1000 weight section to a total of 100 weight sections of a polymer (A) or a polymer (A) and a polymer (D). The following are mentioned as an example of a bulking agent. These bulking agents may be used independently and may be used together two or more sorts.

[0077]Calcium carbonate which carried out the surface treatment of the surface with fatty acid or a resin acid system organic matter, Colloid calcium carbonate with a mean particle diameter of 1 micrometer or less which impalpable-powder-sized this calcium carbonate further, Calcium carbonate, such as precipitated calcium carbonate with a mean particle diameter of 1-3 micrometers manufactured with a sedimentation method, and heavy calcium carbonate with a mean particle diameter of 1-20 micrometers. Fumed silica, sedimentation nature silica, a silicic acid anhydride, hydrous silicic acids, and carbon black, Magnesium carbonate, diatomite, calcination clay, clay, talc, titanium oxide, bentonite, organic bentonite, ferric oxide, a zinc oxide, an active white, a milt balloon, glass balloons, wood flour, pulp, a cotton chip, mica, and blacking wash farina — rubbing — powder state bulking agents, such as farina, graphite, aluminum impalpable powder, and the Flint powder. Fibrous fillers, such as asbestos, glass fiber, a glass filament, carbon fiber, Kevlar fiber, and a polyethylene fiber.

[0078](Plasticizer) A publicly known plasticizer can be used as a plasticizer. The amount of plasticizer used has 0.001 - 1000 preferred weight section to a total of 100 weight sections of a polymer (A) or a polymer (A) and a polymer (D). The following are mentioned as an example of a plasticizer.

[0079]Phthalic ester, such as dioctyl phthalate, dibutyl phthalate, and phthalic acid benzyl butyl ester Aliphatic-carboxylic-acid ester, such as dioctyl adipate, a succinic acid screw (2-methyloxy), dibutyl sebacate, and butyl oleate. Alcohol ester, such as pentaerythritol ester Phosphoric ester, such as trioctyl phosphate and tricresyl phosphate Epoxy plasticizers, such as epoxidized soybean oil, 4,5-epoxy hexahydrophthalic acid dioctyl, and epoxy stearic acid benzyl. A chlorinated paraffin. Polyester plasticizers, such as polyester dibasic acid and dihydric alcohol are made to come to react. Polyether, such as a polyoxypropylene glycol and its derivative. Polymeric plasticizers, such as oligomer, such as the oligomer of styrene systems, such as Poly alpha-methylstyrene and polystyrene, polybutadiene, Butadiene Acrylonitrile, polychloroprene, polyisoprene, polybutene, hydrogenation polybutene, and epoxidation polybutadiene.

[0080](Hardening accelerator catalyst) When stiffening a hardenability constituent in this invention, a hardening accelerator catalyst which promotes a hardening reaction of a hydrolytic basis content silicon group may be used. The following compound is mentioned as a concrete example. Those one sort or two sorts or more are used. As for a hardening accelerator catalyst, it is preferred to carry out 0.001-10 weight-section use to a total of 100 weight sections of a polymer (A) or a polymer (A) and a polymer (D).

[0081]Metal salt, such as an alkyl titanate, an organic silicon titanate, and bismuth tris-2-ethylhexoate, Acidic compounds, such as phosphoric acid, p-toluenesulfonic acid, and phthalic acid, a butylamine, Aliphatic series monoamines, such as hexylamine, octylamine, decyl amine, and lauryl amine, Aliphatic diamine, such as as ethylenediamine and a hexanediamine, diethylenetriamine, Aliphatic polyamine, such as as triethylenetriamine and tetraethylenepentamine. Amine compounds, such as aromatic amine, such as

http://www4.ipdl.inpit.go.jp/cgi-bin/tran_web_cgi_ejje?atw_u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/18

http://www4.indl.innit.go.io/cgi-bin/tran web cgi ejic?atw u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/1

http://www4.ipdl.inp.it/go.jp/cgi-bin/tran_web.cgi/eje?atw_u=http%3A%2F%2Fwww4.ipdl.inp.it... 2011/03/1

[0106]The room-temperature-curing nature constituent of this invention is suitable for the use as which it can be used for sealant, a water blocking material, adhesives, a coating agent, etc., and the dynamic flatness nature to the sufficient cohesive force and adherend of especially the hardened material itself is required.

[0107]

[Working example]The embodiment and comparative example which produced the hardened material are shown below using the polymer (P1-P23) manufactured in the examples 1-23 of manufacture. A part shows a weight section. In the examples 1-13 of manufacture, a hydroxyl value conversion molecular weight shows the molecular weight converted from the hydroxyl value of the polyoxyalkylene polymer which has a hydroxyl group which is a raw material. M_w/M_n is the value measured by the gel permeation chromatograph using a tetrahydrofuran as a solvent. The analytical curve was prepared using the polyoxyalkylene polyol. In the examples 14-17 of manufacture, the molecular weight was measured by the gel permeation chromatograph, using a tetrahydrofuran as a solvent. The analytical curve was prepared using polystyrene.

[0108](Example 1 of manufacture) Glycerin was used as the initiator and the bottom propylene oxide of existence of a zinc hexa cyanocobaltate glyme complex compound catalyst was made to react. The methanol solution of sodium methoxide was added to the polypropylene oxide of hydroxyl value conversion molecular weight 17000 and $M_w/M_n=1.3$, scale loss draft methanol was distilled off, and the terminal hydroxyl groups of polypropylene oxide was changed into sodium alcoholate. Next, the allyl chloride was made to react. The unreacted allyl chloride was removed and refined and allyl group end polypropylene oxide was obtained (let this be the polymer U1.). When the hydroxyl group which remains was analyzed by the measuring method of the hydroxyl value, they were 0.01 millimol /g. The trimethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst to the polymer U1, and the polymer P1 which has an average of two trimethoxysilyl groups at the end was obtained.

[0109](Example 2 of manufacture) The polypropylene oxide of hydroxyl value conversion molecular weight [which used propylene glycol as the initiator, made the bottom propylene oxide of existence of a zinc hexa cyanocobaltate glyme complex compound catalyst react, and was obtained] 17000, and $M_w/M_n=1.3$ is used,

The polypropylene oxide which has an allyl group at the end by the same method as the example 1 of manufacture was obtained (the hydroxyl groups which remain are 0.01 millimols /g). The trimethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst to this reactant, and the polymer P2 which has an average of 1.3 trimethoxysilyl groups at the end was obtained.

[0110](Example 3 of manufacture) The polypropylene oxide of hydroxyl value conversion molecular weight [which used sorbitol as the initiator, made the bottom propylene oxide of existence of a zinc hexa cyanocobaltate glyme complex compound catalyst react, and was obtained] 15000, and $M_w/M_n=1.3$ is used,

The polypropylene oxide which has an allyl group at the end by the same method as the example 1 of manufacture was obtained (the hydroxyl groups which remain are 0.01 millimols /g). The trimethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst to this reactant, and the polymer P3 which has an average of 3.9 trimethoxysilyl groups at the end was obtained.

[0111](Example 4 of manufacture) The mixture which made the mole ratio methyl dimethoxysilane and trimethoxysilane which are hydroxysil compounds, and was mixed in proportion of 30 to 70 is made to react under existence of a platinum catalyst to the polymer U1 manufactured in the example 1 of manufacture, The polymer P4 which has simultaneously an average of 0.6 methyl dimethoxy silyl group and an average of 1.4 trimethoxysilyl groups at the end was obtained.

[0112](Example 5 of manufacture) 3-mercaptopropyltrimethoxysilane which is a silyl compound to the polymer U1 manufactured in the example 1 of manufacture, It was made to react using the 2,2'-azobis 2-methylbutyronitrile which is a polymerization initiator, and the polymer P5 which has an average of two trimethoxysilyl groups at the end was obtained.

[0113](Example 6 of manufacture) It refined, after polymerizing propylene oxide using the zinc hexa cyanocobaltate catalyst by having used glycerin as the initiator and obtaining polyoxypropylene triol of hydroxyl value conversion molecular weight 17000 and $M_w/M_n=1.3$. Isocyanate propyltrimethoxysilane was added to this, the urethane-ized reaction was performed, both ends were changed into the trimethoxysilyl group, and the polymer P6 of the molecular weight 18000 which has an average of two trimethoxysilyl groups at the end was obtained.

[0114](Example 7 of manufacture) To the polymer U1 manufactured in the example 1 of manufacture, methyl dimethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst, and the polymer P7 which has an average of two methyl dimethoxy silyl groups at the end was obtained.

[0115](Example 8 of manufacture) Except using methyldimethoxysilane instead of methyl dimethoxysilane as a

http://www4.ipdl.inpit.go.jp/cgi-bin/tran_web.cgi_ejje?atw_u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/18

hydroxysil compound in the example 7 of manufacture, it carried out like the example 7 of manufacture, and the polymer P9 which has an average of two methyldi ethoxy silyl groups at the end instead of the polymer P7 was obtained.

[0116](Example 9 of manufacture) The polypropylene oxide of hydroxyl value conversion molecular weight [which used propylene glycol as the initiator, made the bottom propylene oxide of existence of a zinc hexa cyanocobaltate glyme complex compound catalyst react, and was obtained] 7000, and $M_w/M_n=1.2$ is used,

The polypropylene oxide which has an allyl group at the end by the same method as the example 1 of manufacture was obtained (the hydroxyl groups which remain are 0.01 millimols /g). Methyl dimethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst to this reactant, and the polymer P9 which has an average of 1.3 methyl dimethoxy silyl groups at the end was obtained.

[0117](Example 10 of manufacture) The polypropylene oxide of hydroxyl value conversion molecular weight [which used propylene glycol as the initiator, made the bottom propylene oxide of existence of a zinc hexa cyanocobaltate glyme complex compound catalyst react, and was obtained] 7000, and $M_w/M_n=1.2$ is used,

The polypropylene oxide which has an allyl group at the end by the same method as the example 1 of manufacture was obtained (the hydroxyl groups which remain are 0.01 millimols /g). The trimethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst to this reactant, and the polymer P10 which has an average of 1.3 trimethoxysilyl groups at the end was obtained.

[0118](Example 11 of manufacture) The methanol solution of sodium methoxide was added to polyoxypropylene diol of the hydroxyl value conversion molecular weight 3000 obtained using the potassium hydroxide catalyst, scale loss draft methanol was distilled off, and terminal hydroxyl groups was changed into sodium alcoholate. Next, the allyl chloride was made to react continuously, after making it react to chlorobromomethane and performing polymer quantification. The unreacted allyl chloride was removed and refined and the polypropylene oxide ($M_w/M_n=1.9$) which has an allyloxy group at the end was obtained (the hydroxyl groups which remain are 0.01 millimols /g). The polymer P11 of the molecular weight 7000 which makes the trimethoxysilane which is a hydroxysil compound react to this under existence of a platinum catalyst, and has an average of 1.3 trimethoxysilyl groups at the end was obtained.

[0119](Example 12 of manufacture) Polyoxypropylene diol of hydroxyl value conversion molecular weight [which was obtained using the potassium hydroxide catalyst] 6000 and $M_w/M_n=1.9$ is used. The polypropylene oxide which has an allyloxy group at the end by the same method as the example 1 of manufacture was obtained (the hydroxyl groups which remain are 0.01 millimols /g). The trimethoxysilane which is a hydroxysil compound was made to react to this under existence of a platinum catalyst, and the polymer P12 which has an average of 1.3 trimethoxysilyl groups at the end was obtained.

[0120](Example 13 of manufacture) To the polymer U1 manufactured in the example 1 of manufacture, triethoxysilane which is a hydroxysil compound was made to react under existence of a platinum catalyst, and the polymer P13 which has an average of two triethoxy silyl groups at the end was obtained.

[0121](Embodiments 1-20 and comparative examples 1-4) Inside of the polymers P1-P13, To 100 copies of polymers shown in Tables 1-3, 100 copies of fatty acid surface treatment calcium carbonate, 50 copies of heavy calcium carbonate, and a plasticizer shown in Tables 1-3 50 copies or zero copy. An ultraviolet ray absorbent, a hindered amine light stabiliser, and an antioxidant which are shown in thixotropy grant agent 3 copy and Tables 1-3 One copy each, Five copies of curing-in-air compounds, three copies of photoresist compounds shown in Tables 1-3, a thing which mixed 0.7 copy of lauryl amine with two copies of 2-ethylhexane tin beforehand as a curing catalyst, or two copies of dibutyltin bisacetylacetonate was added, it mixed uniformly, and a hardenability constituent was obtained.

[0122]Time for constituent viscosity to reach 1,600,000 cps under 20 ±65% humidity conditions was measured for inner-drying-property evaluation of this constituent. It was recuperated under 50 ±6% and 60% humidity under 20 ±6% and 65% humidity in a mullied constituent on the 7th on the 7th, and a 5-mm-thick sheet was obtained. The surface weatherability 250 hours after this sheet and of 500 hours and 750 hours after was investigated with a sunshine weatherometer. Evaluation made ± what O and a hair crack are accepted to in what a surface crack is not accepted to after a sunshine weatherometer examination, and made x what a crack is clearly accepted to. A result is shown in Table 1 - 3.

[0123](End group of a polymer)
TM: A trimethoxysilyl group, DM:methyl dimethoxy-silyl group, TE:triethoxy-silyl group, DE: A methyl dimethoxy silyl group.

[0124](Curing-in-air compound)

A: Tung oil, B:polymerization tung oil (***** No. 4), C:urethane oil (UO-5), D:linseed-oil conversion alkyl

http://www4.ipdl.inpit.go.jp/cgi-bin/tran_web.cgi_ejje?atw_u=http%3A%2F%2Fwww4.ipdl.inpit... 2011/03/18

(HL-20) (A-D: the TOMEN Chemical Co. article), and E: liquid polybutadiene R-15HT (product made from Idemitsu Petrochemistry).

[0125](Photorealist compound)

A: ARONIKUSU M309, B:M400, C:M8060 (A-C: made by Toagosei), D: KAYARAD (made by Nippon Kayaku Co., Ltd.), E:acrylic acid fluoro alkyl (C₈F₁₇C₂H₄) ester, F: acrylic acid fluoro alkyl (C₈F₁₇C₃H₆) ester (E, F: made by Asahi Glass Co., Ltd.).

[0126](Ultraviolet ray absorbent)

A: The tinuvin 3277, B: tinuvin 213 (A, B: Tiba Specialty Chemicals article).

[0127](Hindered amine light stabiliser)

ADEKA stub LA-52, B:ADEKA stub LA-67, D: A: ADEKA stub LA63P (A-D: made by Asahi Denka Kogyo K.K.), E: the tinuvin 144, F: the tinuvin 765, G:CHIMASSOPB119floor line (E-G: made in Tiba Specialty Chemicals), H:SANORULS765 (H: made by Sankyo Co., Ltd.).

[0128](Antioxidant)

A: Styrene-ized phenol (NOKURAKU SP, Ouchi Shinko Chemical), B:2,6-di-tert-butyl-4-methylphenol, C:

IRUGA Nox 245 (B, C: made in Tiba Specialty Chemicals).

[0129](Plasticizer)

A: Di-(2-ethylhexyl)phthalate, B: polyoxypropylene glycol end allyl ether of the molecular weight 10000,

C:4,5-epoxy cyclohexanedicarboxylic acid di(2-ethylhexyl).

[0130](Curing catalyst)

A: A mixture of octylic acid tin and lauryl amine, B: dibutyltin bisacetylacetonate.

[0131](Example 14 of manufacture) Based on a method indicated to JP,1-170681,A, 1,4-bis(1-chloro-1-methylethyl)benzene is used as an initiator. A molecular weight which has an isopropenyl group at a rate of about 92% in both ends which polymerized isobutylene by making boron trichloride into a catalyst, and which carried out back dehydrochlorination and were manufactured makes chloroplatinic acid with a catalyst an isobutylene system polymer of about 5000, and trichlorosilane is made to react in 90 ** 12 hours. The polyisobutylene system polymer P14 which has an average of 1.2 trimethoxysilyl groups at the end by making methanol react to methyl orthoformate furthermore was obtained.

[0132](Example 15 of manufacture) Based on a method indicated to JP,1-170681,A, 1,4-bis(1-chloro-1-methylethyl)benzene is used as an initiator. A molecular weight which has an isopropenyl group at a rate of about 92% in both ends which polymerized isobutylene by making boron trichloride into a catalyst, and which carried out back dehydrochlorination and were manufactured makes chloroplatinic acid with a catalyst an isobutylene system polymer of about 5000, and methylidi chlorosilane is made to react in 90 ** 12 hours. The polyisobutylene system polymer P15 which has an average of 1.2 methyl dimethoxy silyl groups at the end by making methanol react to methyl orthoformate furthermore was obtained.

[0133](Example 16 of manufacture) hydrogenation polybutadiene (polytail HA.) which has a hydroxyl group at the end 90-mol% of 3-isocyanate propyltrimethoxysilane was made to react to the Mitsubishi Chemical terminal hydroxyl groups, and the hydrogenation polybutadiene polymerization object P16 which has an average of 1.3 trimethoxysilyl groups at the end was acquired.

[0134](Example 17 of manufacture) hydrogenation polybutadiene (polytail HA.) which has a hydroxyl group at the end 90-mol% of 3-isocyanate propylmethyl dimethoxysilane was made to react to the Mitsubishi Chemical terminal hydroxyl groups, and the hydrogenation polybutadiene polymerization object P17 which has an average of 1.3 methyl dimethoxy silyl groups at the end was acquired.

[0135](Embodiments 21-27 and comparative examples 5-7) Inside of the polymers P14-P17, To 100 copies of polymers shown in Tables 4 and 5, 100 copies of colloid calcium carbonate, 40 copies of heavy calcium carbonate, 65 copies of hydrocarbon system retarder thinner (Nippon Oil Chemical industry high ZORU), Five copies of sodium sulfate hydrates, dripping stop agent 1 copy, five copies of curing-in-air compounds, three copies of photorealist compounds, one copy of ultraviolet ray absorbent, one copy of hindered amine light stabiliser, and one copy of antioxidant are added. A mixture of two copies of octylic acid tin and 0.7 copy of lauryl amine or two copies of dibutyltin bisacetylacetonate was mixed, and it was considered as a hardenability constituent.

[0136]The examination same about this constituent as Embodiments 1-20 was done. A result is shown in Tables 4 and 5.

[0137](Example 18 of manufacture) 100 g of the polymer P1 was put into a reactor with a churning group, and it heated at 100 **, and it added over 3 hours from a dropping funnel there, agitating a solution of 15 g of acrylonitrile, 15g of styrene, and 0.3 g of 2,2'-azobisisobutyronitrile. After continuing heating and stirring at 100 ** for further 2 hours, degassing operation was performed under decompression and the polymer

mixture P18 of a letter of nebula was obtained.

[0138](Example 20 of manufacture) 50g of the polymer P1 and 50 g of the polymer P7 were put into a reactor with an agitator, and 50 g of toluene was added and diluted. Heat this mixture at 100 ** and 20 g of acrylonitrile, 20 g of styrene, A solution which dissolved the 2,2'-azobisisobutyronitriles 0 and 3g was dropped at 5 g of glycidyl methacrylate, and 2 g of 3-methacryloyl oxypropyl trimethoxysilane under churning over 3 hours. After a 2,2'-azobisisobutyronitriles [0 and 2g] toluene solution was dropped at an end of dropping back pan over 30 minutes, it heated and stirred at 100 ** for 3 hours. Toluene was distilled out of an obtained mixture under 100 ** decompression, and the polymer mixture P20 of a letter of nebula was obtained.

[0139](Example 22 of manufacture) 100 g of the polymer P13 was put into a reactor with an agitator. Heat this at 100 ** and 5 g of styrene, 10 g of methyl methacrylate, A solution which dissolved 7 g of butyl methacrylate, 2 g of methacrylic acid octadecyl, 18 g of 3-methacryloyl oxypropyl trimethoxysilane, and 0.5 g of 2,2'-azobisisobutyronitrile was dropped under churning over 3 hours. After a toluene solution of 0.2 g of 2,2'-azobisisobutyronitrile was dropped at an end of dropping back pan over 30 minutes, it heated and stirred at 100 ** for 3 hours. Toluene was distilled out of an obtained mixture under 100 ** decompression, and the polymer mixture P22 of a letter of nebula was obtained.

[0140](Example 23 of manufacture) The polymer P23 was manufactured like the example 22 of manufacture except replacing a raw material with the polymer P13, and using the polymer P8 (methylidi ethoxy silyl group end).

[0141](Embodiments 28-34 and comparative examples 8-10) Inside of the polymers P18-P23, To 100 copies of polymers shown in Tables 6 and 7, 100 copies of colloid calcium carbonate, 40 copies of heavy calcium carbonate, 30 copies of plasticizers or zero copy, five copies of sodium sulfate hydrates, Dripping stop agent 1 copy, five copies of curing-in-air compounds, three copies of photorealist compounds, one copy of ultraviolet ray absorbent, One copy of hindered amine light stabiliser and one copy of antioxidant were added, and further, a mixture of two copies of octylic acid tin and 0.7 copy of lauryl amine or two copies of dibutyltin bisacetylacetonate was mixed, and it was considered as a hardenability constituent. The examination same about this constituent as Embodiments 1-20 was done. A result is shown in Tables 6 and 7.

[0142]

[Table 1]

	実施例1	実施例2	実施例3	実施例4	実施例5	実施例6	実施例7	実施例8	実施例9
重合体	P1	P1	P1	P1	P1	P1	P1	P1	P2
重合体末端基	TM	TM	TM	TM	TM	TM	TM	TM	TM
空気硬化性化合物	A	B	C	D	E	A	A	A	A
光硬化性化合物	A	A	B	B	C	D	A+E	A+F	A
紫外線吸収剤	A	A	A	A	B	B	B	B	A
光安定剤	B	A	C	D	E	F	G	H	B
酸化防止剤	C	A	B	A	A	B	C	C	A
可塑剤	A+C	A+C	A+C	A+C	A+C	A	A+C	B	A+C
	(1:1)	(1:1)	(1:1)	(1:1)	(1:1)	(1:1)	(1:1)	(1:1)	(1:1)
酸化防止剤	A	A	A	A	A	B	A	B	A
100万分散液	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
時間(分)									
表面	500 hr	○	○	○	○	○	○	○	○
経路	500 hr	○	○	○	○	○	○	○	○
性	750 hr	○	○	○	○	○	○	○	○

[0143]

[Table 2]

	実施 例 10	実施 例 11	実施 例 12	実施 例 13	実施 例 14	実施 例 15	実施 例 16	実施 例 17	実施 例 18
重合体	P3	P4	P5	P6	P10	P11	P12	P13	P1
重合体末端基	TM	TM/DM	TM	TM	TM	TM	TM	TE	TM
空気酸化性 化合物	A	A	A	A	B	B	B	B	A
光硬化性 化合物	A	A	A	A	A	A	A	A	A+P (1:1)
紫外線吸収剤	A	A	A	A	A	A	A	A	B
光安定剤	B	B	D	D	D	E	E	E	H
酸化防止剤	A	B	B	C	C	C	C	C	C
可塑剤	C	C	A+C	A	A	B	B	B	なし
	(1:1)	(1:1)	(1:1)						
硬化触媒	A	A	A	B	B	B	B	B	B
160万cps流動時間 時間(秒)	0.5	1	0.5	0.5	0.5	1.5	1.5	1	0.5
表面	250 hr	○	○	○	○	○	○	○	○
耐熱	500 hr	○	○	○	○	○	○	○	○
性	750 hr	○	○	○	○	○	○	○	○

[0144]

[Table 3]

	実施 例 19	実施 例 20	比較 例 1	比較 例 2	比較 例 3	比較 例 4
重合体	P1	P1	P7	P8	P9	P1
重合体末端基	TM	TM	DM	DE	DM	TM
空気酸化性化合物	なし	A	A	B	B	なし
光硬化性化合物	A	なし	A	A	A	なし
紫外線吸収剤	A	A	A	A	A	A
光安定剤	B	B	B	E	D	B
酸化防止剤	C	C	C	C	C	C
可塑剤	A+C	A+C	A+C	B	A	A+C
	(1:1)	(1:1)	(1:1)			(1:1)
硬化触媒	A	A	A	B	B	A
160万cps流動時間 時間(秒)	0.5	0.5	4	8	7	0.5
表面	250 hr	○	○	○	○	△
耐熱性	500 hr	○	○	○	○	△
	750 hr	△	△	○	○	△~×

[0145]

[Table 4]

	実施 例 21	実施 例 22	実施 例 23	実施 例 24	実施 例 25
重合体	P14	P14	P16	P14/P15 (1:1)	P14/P15 (1:1)
重合体末端基	TM	TM	TM	TM/DM	TM/DM
空気酸化性化合物	A	A	A	A	A
光硬化性化合物	A	A	A	A	A
紫外線吸収剤	A	A	A	A	A
光安定剤	B	B	B	B	B
酸化防止剤	C	C	C	C	C
硬化触媒	A	B	A	A	B
160万cps流動時間 (秒)	1	0.5	1	2	1.5
表面	1900 hr	○	○	○	○
耐熱	2000 hr	○	○	○	○
性	3000 hr	○	○	○	○

[0146]

[Table 5]

	実施 例 26	実施 例 27	比較 例 5	比較 例 6	比較 例 7
重合体	P14	P14	P15	P17	P14
重合体末端基	TM	TM	DM	DM	TM
空気酸化性化合物	なし	A	A	A	なし
光硬化性化合物	A	なし	A	A	なし
紫外線吸収剤	A	A	A	A	A
光安定剤	B	B	B	B	B
酸化防止剤	C	C	C	C	C
硬化触媒	A	B	A	A	A
160万cps流動時間 (秒)	1	0.5	4.5	5	1
表面	1000 hr	○	○	○	△
耐熱	2000 hr	○~△	○	○	△
性	3000 hr	△	△	○	×

[0147]

[Table 6]

	実施例 28	実施例 29	実施例 30	実施例 31	実施例 32
重合体	P18	P18	P18	P20	P22
重合体末端基	TM	TM	TM	TM/DM	TE
空気酸化性化合物	A	B	B	A	B
光酸化性化合物	A	A	A	B	A
紫外線吸収剤	A	A	A	A	A
光安定剤	B	A	A	C	E
酸化防止剤	C	A	A	B	C
可塑剤	A+C (1:1)	B	なし	A+C (1:1)	B
硬化触媒	A	B	B	A	B
160万cps:通過時間	0.5	0.5	0.5	0.5	0.5
(b)					
表面耐 250 hr	O	O	O	O	O
候性 500 hr	O	O	O	O	O
750 hr	O	O	O	O	O

[0148]

[Table 7]

	実施例 33	実施例 34	比較例 8	比較例 9	比較例 10
重合体	P18	P18	P21	P23	P18
重合体末端基	TM	TM	DM	DE	TM
空気酸化性化合物	なし	A	A	B	なし
光酸化性化合物	A	なし	B	A	なし
紫外線吸収剤	A	A	A	A	A
光安定剤	B	B	C	E	B
酸化防止剤	C	C	B	C	C
可塑剤	A+C (1:1)	A+C (1:1)	A+C (1:1)	B (1:1)	A+C (1:1)
硬化触媒	A	A	A	B	A
160万cps:通過時間	0.5	0.5	3	4.5	0.5
(b)					
表面耐 250 hr	O	O	O	O	Δ
候性 500 hr	Δ	O	O	O	O~Δ
750 hr	Δ	Δ	O	O	Δ~X

[0149]

[Effect of the Invention]The room-temperature-curing nature constituent of this invention has the effect of excelling in hardenability and surface weatherability extremely.

[Translation done.]

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号
特開2000-136313
(P2000-136313A)

(43) 公開日 平成12年5月16日 (2000.5.16)

(51) Int.Cl.⁷

識別記号

F I

テーマコード(参考)

C 0 8 L 101/10
65/00

C 0 8 L 101/10
65/00

4 J 0 0 2

審査請求 未請求 請求項の数12 O L (全 18 頁)

(21) 出願番号

特願平10-313557

(22) 出願日

平成10年11月4日 (1998. 11. 4)

(71) 出願人 000000044

旭硝子株式会社

東京都千代田区有楽町一丁目12番1号

(72) 発明者 土居 孝夫

神奈川県横浜市神奈川区羽沢町1150番地

旭硝子株式会社内

(72) 発明者 渡部 崇

神奈川県横浜市神奈川区羽沢町1150番地

旭硝子株式会社内

(72) 発明者 小野口 竜夫

神奈川県横浜市神奈川区羽沢町1150番地

旭硝子株式会社内

最終頁に続く

(54) 【発明の名称】 室温硬化性組成物

(57) 【要約】


【課題】 硬化性および表面耐候性に優れる室温硬化性組成物の提供。

【解決手段】 3つの加水分解性基がケイ素に結合した加水分解性ケイ素基を必須成分として有する重合体

(A)、および空気硬化性化合物 (K) および/または光硬化性化合物 (L) からなる室温硬化性組成物。

【特許請求の範囲】

【請求項1】下記式(1)で表される加水分解性ケイ素基を有する重合体であって、該重合体の一部または全部が式(1)のaが3である加水分解性ケイ素基を有する重合体である重合体(A)、空気硬化性化合物(K)および/または光硬化性化合物(L)を必須成分とする室温硬化性組成物。



(式(1)中、 R^1 は炭素数1~20の置換または非置換の1価の有機基、Xは水酸基または加水分解性基、aは1、2または3を示す。ただし、 R^1 が複数個存在するときは、それらの R^1 は同じでも異なってもよく、Xが複数個存在するときは、それらのXは同じでも異なってもよい。)

【請求項2】重合体(A)の分子量が8000~50000である、請求項1記載の室温硬化性組成物。

【請求項3】重合体(A)が、式(1)で表される加水分解性ケイ素基を有するポリオキシアルキレン重合体

(B)である、請求項1または2記載の室温硬化性組成物。

【請求項4】ポリオキシアルキレン重合体(B)の分子量分布 M_w/M_n が1.7以下である、請求項3記載の室温硬化性組成物。

【請求項5】ポリオキシアルキレン重合体(B)が、開始剤の存在下、複合金属シアン化物錯体を触媒として環状エーテルを重合させて得られるポリオキシアルキレン重合体の末端に、式(1)で表される加水分解性ケイ素基を導入して得られる重合体である、請求項3または4記載の室温硬化性組成物。

【請求項6】ポリオキシアルキレン重合体(B)が、開始剤の存在下、環状エーテルを重合させて得られる、分子量分布 M_w/M_n が1.7以下であるポリオキシアルキレン重合体の末端に、式(1)で表される加水分解性ケイ素基を導入して得られる重合体である、請求項3、4または5記載の室温硬化性組成物。

【請求項7】ポリオキシアルキレン重合体(B)が、さらに、重合性不飽和基含有単量体(C)を重合して得られる重合体(D)を含有する、請求項3、4、5または6記載の室温硬化性組成物。

【請求項8】ポリオキシアルキレン重合体(B)が、さらに、ポリオキシアルキレン重合体(B)中で重合性不飽和基含有単量体(C)を重合して得られる重合体(D)を含有する、請求項3、4、5または6記載の室温硬化性組成物。

【請求項9】重合性不飽和基含有単量体(C)の一部または全部が、重合性不飽和基を有し、かつ、グリシジル基および/または式(1)で表される加水分解性ケイ素基を有する単量体である、請求項7または8記載の室温硬化性組成物。

【請求項10】重合体(A)の一部または全部が、式

(1)中のaが1または2である加水分解性ケイ素基および式(1)中のaが3である加水分解性ケイ素基を併有する重合体である、請求項1、2、3、5、6、7、8または9記載の室温硬化性組成物。

【請求項11】重合体(A)が、式(1)中のaが1または2である加水分解性ケイ素基を有する重合体および式(1)中のaが3である加水分解性ケイ素基を有する重合体の両方を含有する、請求項1、2、3、5、6、7、8または9記載の室温硬化性組成物。

【請求項12】重合体(A)が、加水分解性ケイ素基として式(1)中のaが3である加水分解性ケイ素基のみを有する重合体である、請求項1、2、3、5、6、7、8または9記載の室温硬化性組成物。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】本発明は湿分存在下で硬化する硬化性組成物に関する。

【0002】

【従来の技術】末端に加水分解性ケイ素基を有するポリオキシアルキレン重合体は、硬化物がゴム弾性を有するという特徴を生かし被覆組成物・密封組成物などの用途に用いられている。

【0003】

【発明が解決しようとする課題】末端に加水分解性ケイ素基を有する各種の重合体を硬化させてシーラント、接着剤などに使用する方法はよく知られており、工業的に有用な方法である。このような重合体のうち、特に主鎖がポリオキシアルキレンである重合体は、室温で液状であり、かつ硬化物が比較的低温でも柔軟性を保持し、シーラント、接着剤などに利用する場合好ましい特性を備えている。

【0004】そのような湿分硬化性の重合体としては、特公昭61-18582、特開平3-72527や特開平3-47825に記載されている、末端に加水分解性ケイ素基を有する重合体であって、伸びや柔軟性を保持するためにケイ素原子1つ当たり2つの加水分解性基が結合してなる加水分解性ケイ素基を有する重合体や、特公昭58-10418および特公昭58-10430に記載されている、ケイ素原子1つ当たり3つの加水分解性基が結合してなる加水分解性ケイ素基を有する重合体であって、分子量が6000以下の比較的低分子量の重合体が知られている。

【0005】しかしながら、このような重合体は接着剤の用途などや低温で使用する場合など、特に非常に速い硬化速度を必要とする場合その硬化速度は充分ではなく、また硬化後の柔軟性を出したい場合には、架橋密度を低下させる必要があり、そのため架橋密度が充分でないためにべたつき(表面タック)があり、また耐候劣化により長期的には表面にクラックが入りやすい、という問題があった。この問題を解決するために、光硬化性化

10

20

30

40

50

合物や空気硬化性化合物を添加する方法が特公昭 62-26349、特開平 1-198661、特開平 2-117954、特開平 3-160053、特開平 5-70531、特開平 5-65400、特開平 5-65407、特開平 7-196909、特開平 8-269315 などで試みられており、特に特開平 5-65400、特開平 5-65407 には分子量分布の狭い重合体を使用する例が記載されている。しかしながら、これら公知の例は実質的には硬化性官能基としてモノアルキルジアルコキシシリル基での例が知られているにすぎず、そのような場合硬化速度を速くすることは困難であった。

【0006】以上のように、加水分解性ケイ素基を有する重合体に対して、その柔軟性や作業性を大きく悪化させることなく非常に速い硬化特性と表面耐候性が改良できる組成が望まれていた。

【0007】

【課題を解決するための手段】本発明は、特定の空気硬化性化合物や光硬化性化合物を用いることによる、硬化特性および表面耐候性にきわめて優れた室温硬化性組成物に関する下記の発明である。

【0008】下記式(1)で表される加水分解性ケイ素基を有する重合体であって、該重合体の一部または全部が式(1)のaが3である加水分解性ケイ素基を有する重合体である重合体(A)、空気硬化性化合物(K)および/または光硬化性化合物(L)を必須成分とする室温硬化性組成物。

【0009】 $-SiX_a.R^{1-3}_a \dots (1)$

(式(1)中、 R^1 は炭素数1~20の置換または非置換の1価の有機基、Xは水酸基または加水分解性基、aは1、2または3を示す。ただし、 R^1 が複数個存在するときは、それらの R^1 は同じでも異なってもよく、Xが複数個存在するときは、それらのXは同じでも異なってもよい。)

【0010】(重合体(A))本発明において、重合体(A)の主鎖としては、ポリオキシアルキレン、ポリエステル、ポリカーボネート、ポリオレフィンなどが挙げられるが、本質的に主鎖がポリオキシアルキレンからなることが特に好ましい。以下、重合体(A)のうち主鎖がポリオキシアルキレンである重合体(以下、ポリオキシアルキレン重合体(B)という)について代表して説明する。

【0011】(ポリオキシアルキレン重合体(B))式(1)で表される加水分解性ケイ素基を有するポリオキシアルキレン重合体(B)は、たとえば特開平 3-47825、特開平 3-72527、特開平 3-79627 などに提案されている。ポリオキシアルキレン重合体(B)は以下に述べるように、官能基を有するポリオキシアルキレン重合体を原料とし、その末端に有機基を介してまたは介さずして加水分解性ケイ素基を導入して製造されることが好ましい。

【0012】原料ポリオキシアルキレン重合体としては、触媒の存在下かつ開始剤の存在下、環状エーテルなどを反応させて製造される水酸基末端のものが好ましい。開始剤としては1つ以上の水酸基を有するヒドロキシ化合物などが使用できる。環状エーテルとしてはエチレンオキシド、プロピレンオキシド、ブチレンオキシド、ヘキシレンオキシド、テトラヒドロフランなどが挙げられる。触媒としては、カリウム系化合物やセシウム系化合物などのアルカリ金属触媒、複合金属シアン化物錯体触媒、金属ポルフィリン触媒などが挙げられる。

【0013】本発明においては、原料ポリオキシアルキレン重合体として分子量8000~50000の高分子量のポリオキシアルキレン重合体を使用することが好ましい。したがってアルカリ触媒などを用いて製造した比較的分子量のポリオキシアルキレン重合体に塩化メチレンなどの多ハロゲン化合物を反応させることにより多量化して得られるポリオキシアルキレン重合体や複合金属シアン化物錯体触媒を用いて製造したポリオキシアルキレン重合体を使用することが好ましい。

【0014】また、特に重量平均分子量(M_w)および数平均分子量(M_n)の比 M_w/M_n が1.7以下のポリオキシアルキレン重合体を使用することが好ましく、 M_w/M_n は1.6以下であることがさらに好ましく、 M_w/M_n は1.5以下であることが特に好ましい。

【0015】本発明の加水分解性ケイ素基を有するポリオキシアルキレン重合体(B)はこのようなポリオキシアルキレン重合体を原料としてさらに末端基を変性して加水分解性ケイ素基とすることによって得られる。原料ポリオキシアルキレン重合体の M_w/M_n が小さいほど、それを原料として得られるポリオキシアルキレン重合体(B)を硬化させた場合、弾性率が同じものでも硬化物の伸びが大きく高強度となり、かつ重合体の粘度が低くなり作業性に優れる。このようなポリオキシアルキレン重合体のなかでは特に複合金属シアン化物錯体を触媒として開始剤の存在下、アルキレンオキシドを重合させて得られるものが特に好ましく、そのようなアルキレンオキシド重合体の末端を変性して加水分解性ケイ素基としたものが最も好ましい。

【0016】複合金属シアン化物錯体としては亜鉛ヘキサシアノコバルテートを主成分とする錯体が好ましく、なかでもエーテルおよび/またはアルコール錯体が好ましい。その組成は本質的に特公昭 46-27250に記載されているものが使用できる。この場合、エーテルとしてはエチレングリコールジメチルエーテル(グライム)、ジエチレングリコールジメチルエーテル(ジグライム)などが好ましく、錯体の製造時の取り扱いの点からグライムが特に好ましい。アルコールとしてはt-ブタノールが好ましい。


【0017】原料ポリオキシアルキレン重合体の官能基数は2以上が好ましい。硬化物特性として柔軟性を大き

くしたい場合には原料ポリオキシアルキレン重合体の官能基数は2または3が特に好ましい。良好な接着性や硬化性を得る場合には原料ポリオキシアルキレン重合体の官能基数は3~8が特に好ましい。

【0018】原料ポリオキシアルキレン重合体としては、具体的にはポリオキシエチレン、ポリオキシプロピレン、ポリオキシブチレン、ポリオキシヘキシレン、ポリオキシテトラメチレンおよび2種以上の環状エーテルの共重合物が挙げられる。

【0019】特に好ましい原料ポリオキシアルキレン重合体は2~6価のポリオキシプロピレンポリオールであり、特にポリオキシプロピレンジオールとポリオキシプロピレントリオールである。また、下記(イ)や(二)の方法に用いる場合、アリル末端ポリオキシプロピレンモノオールなどのオレフィン末端のポリオキシアルキレン重合体も使用できる。

【0020】該ポリオキシアルキレン重合体(B)は、分子鎖の末端または側鎖に下記式(1)で表される加水分解性ケイ素基を有する。



(式(1)中、 R^1 、 R^1 は炭素数1~20の置換または非置換の1価の有機基であり、Xは水酸基または加水分解性基であり、aは1、2または3である。ただし、 R^1 が複数個存在するときはそれらの R^1 は同じでも異なってもよく、Xが複数個存在するときはそれらのXは同じでも異なってもよい。)

【0021】式(1)で表される加水分解性ケイ素基は、通常有機基を介して、原料ポリオキシアルキレン重合体に導入される。すなわち、ポリオキシアルキレン重合体(B)は式(2)で表される基を有することが好ましい。



(式(2)中、 R^0 は2価の有機基、 R^1 、X、aは上記に同じ。)

【0022】式(1)、(2)中 R^1 は炭素数1~20の置換または非置換の1価の有機基であり、好ましくは炭素数8以下のアルキル基、フェニル基またはフルオロアルキル基であり、特に好ましくは、メチル基、エチル基、プロピル基、ブチル基、ヘキシル基、シクロヘキシル基、フェニル基などである。 R^1 が複数個存在するときはそれらの R^1 は同じでも異なってもよい。

【0023】Xにおける加水分解性基としては、たとえばハロゲン原子、アルコキシ基、アシルオキシ基、アルケニルオキシ基、カルバモイル基、アミノ基、アミノオキシ基、ケトキシメート基などが挙げられる。


【0024】これらのうち炭素原子を有する加水分解性基の炭素数は6以下が好ましく、4以下が特に好ましい。好ましいXとしては炭素数4以下のアルコキシ基やアルケニルオキシ基、特にメトキシ基、エトキシ基、プロポキシ基またはプロペニルオキシ基が例示できる。ま

たXが複数個存在するときはそれらのXは同じでも異なってもよい。

【0025】aは1、2または3である。重合体1分子中の加水分解性ケイ素基の数は1~8が好ましく、2~6が特に好ましい。

【0026】原料ポリオキシアルキレン重合体へ加水分解性ケイ素基を導入する方法は特に限定されないが、たとえば以下の(イ)~(二)の方法で導入できる。

【0027】(イ)水酸基を有するポリオキシアルキレン重合体の末端に、オレフィン基を導入した後、式(3)で表されるヒドロシリル化合物を反応させる方法。




(式(3)中、 R^1 、X、aは前記に同じ。)

【0028】オレフィン基を導入する方法としては、不飽和基および官能基を有する化合物を、水酸基を有するポリオキシアルキレン重合体の末端水酸基に反応させて、エーテル結合、エステル結合、ウレタン結合またはカーボネート結合などにより結合させる方法が挙げられる。アルキレンオキシドを重合する際に、アリルグリシジルエーテルなどのオレフィン基含有エポキシ化合物を添加して共重合させることにより原料ポリオキシアルキレン重合体の側鎖にオレフィン基を導入する方法も使用できる。


【0029】また、ヒドロシリル化合物を反応させる際には、白金系触媒、ロジウム系触媒、コバルト系触媒、パラジウム系触媒、ニッケル系触媒などの触媒を使用できる。塩化白金酸、白金金属、塩化白金、白金オレフィン錯体などの白金系触媒が好ましい。また、ヒドロシリル化合物を反応させる反応は、30~150℃、好ましくは60~120℃の温度で数時間行うことが好ましい。

【0030】(ロ)水酸基を有するポリオキシアルキレン重合体の末端に式(4)で表される化合物を反応させる方法。



(式(4)中、 R^1 、X、aは前記に同じ。 R^2 は炭素数1~17の2価炭化水素基。)上記反応の際には、公知のウレタン化触媒を用いてもよい。また上記反応は20~200℃、好ましくは50~150℃の温度で数時間行うことが好ましい。

【0031】(ハ)水酸基を有するポリオキシアルキレン重合体の末端にトリレンジイソシアネートなどのポリイソシアネート化合物を反応させてイソシアネート基末端とした後、該イソシアネート基に式(5)で表されるケイ素化合物のW基を反応させる方法。



(式(5)中、 R^1 、 R^2 、X、aは前記に同じ。Wは水酸基、カルボキシル基、メルカプト基およびアミノ基(1級または2級)から選ばれる活性水素含有基。)

【0032】(二) 水酸基を有するポリオキシアルキレン重合体の末端にオレフィン基を導入した後、そのオレフィン基と、Wがメルカプト基である式(5)で表されるケイ素化合物のメルカプト基を反応させる方法。

【0033】Wがメルカプト基である式(5)で表されるケイ素化合物としては、3-メルカプトプロピルトリメトキシシラン、3-メルカプトプロピルメチルジメトキシシラン、3-メルカプトプロピルジメチルメトキシシラン、3-メルカプトプロピルトリエトキシシラン、などが挙げられる。

【0034】上記反応の際には、ラジカル発生剤などの重合開始剤を用いてもよく、場合によっては重合開始剤を用いることなく放射線や熱によって反応させてもよい。重合開始剤としては、たとえばパーオキシド系、アゾ系、またはレドックス系の重合開始剤や金属化合物触媒などが挙げられる。重合開始剤としては具体的には、2, 2'-アゾビスイソブチロニトリル、2, 2'-アゾビス-2-メチルブチロニトリル、ベンゾイルパーオキシド、t-アルキルパーオキシエステル、アセチルパーオキシド、ジイソプロピルパーオキシカーボネートなどが挙げられる。また上記反応は20~200℃、好ましくは50~150℃で数時間~数十時間行うことが好ましい。

【0035】(主鎖がポリオキシアルキレン重合体以外である場合) 重合体(A)の主鎖が、ポリエステル、ポリカーボネートの場合、それぞれ水酸基末端のポリエステル、水酸基末端のポリカーボネートを原料として、ポリオキシアルキレン重合体(B)と同様の製法で製造できる。

【0036】主鎖がポリオレフィンの場合、ポリブタジエンポリオールや水添ポリブタジエンポリオールなどの水酸基末端のポリオレフィンを原料としてポリオキシアルキレン重合体(B)と同様の製法で製造できる。また、1, 4-ビス(1-クロロ-1-メチルエチル)ベンゼンを開始剤とし三塩化ホウ素を触媒としイソブチレンを重合させた後、脱塩化水素反応させて製造した、末端にイソプロペニル基を有するイソブチレン系重合体を原料として、ポリオキシアルキレン重合体(B)と同様の製法で製造できる。

【0037】(式(1)中のaが3である加水分解性ケイ素基) 本発明における重合体(A)は一部または全部が「式(1)中のaが3である加水分解性ケイ素基」

(以下、「加水分解性ケイ素基(E)」という)を有する重合体であることを要する。

【0038】「加水分解性ケイ素基(E)」としては、式(1)中のXが炭素数4以下のアルコキシ基である基、すなわち、炭素数4以下のアルコキシ基を有するトリアルコキシシリル基が特に好ましい。トリアルコキシシリル基を有する重合体は非常に反応性が高く、特に初期の硬化速度が非常に速い。

【0039】通常、式(1)で表される加水分解性ケイ素基における加水分解反応においては、水との反応によりシラノール基を発生し($-SiX + H_2O \rightarrow -SiOH + HX$ で表されるシラノール基発生反応)、さらに生じたシラノール基どうしが縮合、またはシラノール基と加水分解性ケイ素基を縮合してシロキサン結合を生じる反応(縮合反応)によって進むと考えられている。いったんシラノール基が発生した後は、縮合反応は順調に進むと考えられる。トリアルコキシシリル基は、アルキルジアルコキシシリル基またはジアルキルアルコキシシリル基と比較して、シラノール基発生反応の初期における反応速度がきわめて速い。したがって、本発明の硬化性組成物は、短時間で十分な強度特性を発現し、特に接着性発現に至るまでの時間が短いという効果を有すると考えられる。

【0040】またトリアルコキシシリル基のうち、炭素数が小さいアルコキシ基を有するトリアルコキシシリル基の方が、炭素数の大きいアルコキシ基を有するトリアルコキシシリル基よりもシラノール基発生反応の初期における反応速度が速いため好ましく、トリメトキシシリル基、トリエトキシシリル基がより好ましく、トリメトキシシリル基がシラノール基発生反応の初期における反応速度がきわめて速いため最も好ましい。したがって、「加水分解性ケイ素基(E)」としてはトリメトキシシリル基であることが最も好ましい。また、重合体(A)中の、式(1)で表される加水分解性ケイ素基中における加水分解性ケイ素基(E)の割合は、用途、必要とする特性などに応じて変える。

【0041】重合体(A)が、該加水分解性ケイ素基として加水分解性ケイ素基(E)のみを有する重合体である場合、すなわち、重合体(A)における式(1)で表される加水分解性ケイ素基のほぼ100%(すなわち80~100%)が加水分解性ケイ素基(E)である場合には、硬化速度が大きいという効果があり、接着性発現に至る硬化性が特に優れた室温硬化性組成物が得られる。この場合、式(1)で表される加水分解性ケイ素基(E)の90~100%、特に95~100%が、加水分解性ケイ素基(E)であることが好ましい。

【0042】また、式(1)中のaが1または2である加水分解性ケイ素基と加水分解性ケイ素基(E)が混在している場合には、良好な伸び特性と速硬化性を両立しうる室温硬化性組成物が得られる。

【0043】この場合、重合体(A)における、式(1)で表される全加水分解性ケイ素基中の加水分解性ケイ素基(E)の割合が5~80%であることが好ましい。この割合を任意に変えることにより要求に応じた特性を自由に制御できる。すなわち加水分解性ケイ素基(E)の割合が5~50%のときは、硬化性を向上させるとともにシーラントなどで必要とされる良好な伸び特性や柔軟性を提供できる。また加水分解性ケイ素基

(E) の割合が 50~80% のときは、弾性接着剤などに必要とされる伸び特性を十分に確保できかつ飛躍的に硬化性を改善できる。

【0044】また、式(1)で表される加水分解性ケイ素基中において加水分解性ケイ素基(E)以外の加水分解性ケイ素基は式(1)中のaが2の加水分解性ケイ素基であることが特に好ましい。炭素数4以下のアルコキシ基を有するジアルコキシアルキルシリル基であることが特に好ましい。ジメトキシメチルシリル基が最も好ましい。

【0045】式(1)中のaが1または2である加水分解性ケイ素基と加水分解性ケイ素基(E)が混在した、重合体(A)を得る方法には、たとえば、下記の方法(ホ)、(ヘ)があり、(ホ)、(ヘ)の方法を併用してもよい。

(ホ) 重合体(A)として、式(1)中のaが1または2である加水分解性ケイ素基および加水分解性ケイ素基(E)を併有する重合体を使用する。

(ヘ) 重合体(A)として、式(1)中のaが1または2である加水分解性ケイ素基を有するポリオキシアルキレン重合体(B)および加水分解性ケイ素基(E)を有する重合体(A)の両方を使用する。


【0046】本発明における重合体(A)の分子量は、その使用される用途に応じて適当な値を選択できるが、重合体(A)の分子量は8000~50000であることが好ましい。

【0047】柔軟性が重視されるシーラントなどの用途には、分子量8000~50000の重合体が好ましい。分子量は、8000~25000であることが特に好ましく、12000~20000であることが最も好ましい。また強度が要求される接着剤などの用途には、分子量8000~30000の重合体が好ましい。8000より低い場合は硬化物が脆いものとなり30000を超える場合は高粘度のため作業性が著しく悪くなる。分子量は8000~20000であることがより好ましく、12000~20000であることが特に好ましい。

【0048】(重合性不飽和基含有単量体(C)を重合して得られる重合体(D))重合体(A)を必須成分とする、室温硬化性組成物は硬化性に優れる。本発明においては、重合体(A)のうち、ポリオキシアルキレン重合体(B)を使用する場合は、ポリオキシアルキレン重合体(B)が、さらに重合性不飽和基含有単量体(C)を重合して得られる重合体(D)を含有することが好ましい。重合体(D)を含有することにより、硬化反応の初期段階における接着性付与の効果、すなわち、接着強度を発現するまでの時間がきわめて短くなる効果が得られる。

【0049】重合性不飽和基含有単量体(C)の代表的なものとしては、たとえば下記式(6)で示される化合

物が挙げられるが、これらに限定されない。




(式中、R、R³、R⁴、R⁵はそれぞれ独立に、水素原子、ハロゲン原子または1価の有機基である。)

【0050】R、R⁵における有機基としては炭素数1~10の1価の置換または非置換の炭化水素基であることが好ましい。R、R⁵はそれぞれ水素原子であることがより好ましい。R³、R⁴における有機基は炭素数1~10の1価の置換または非置換の炭化水素基、アルコキシ基、カルボキシ基、アルコキシカルボニル基、シアノ基、シアノ基含有基、アルケニル基、アシルオキシ基、カルバモイル基、ピリジル基、グリシジルオキシ基またはグリシジルオキシカルボニル基であることが好ましい。R³は水素原子、ハロゲン原子または炭素数1~10の1価の置換または非置換の炭化水素基であることが特に好ましい。

【0051】重合性不飽和基含有単量体(C)の具体例としては、スチレン、α-メチルスチレン、クロロスチレンなどのスチレン系単量体；アクリル酸、メタクリル酸、アクリル酸メチル、メタクリル酸メチル、アクリル酸エチル、メタクリル酸エチル、アクリル酸ブチル、メタクリル酸ブチル、アクリル酸2-エチルヘキシル、メタクリル酸2-エチルヘキシル、アクリル酸ベンジル、メタクリル酸ベンジルなどのアクリル酸、メタクリル酸またはそのエステル、アクリルアミド、メタクリルアミドなどのアクリル系単量体；アクリロニトリル、2,4-ジシアノブテン-1などのシアノ基含有単量体；酢酸ビニル、プロピオン酸ビニルなどのビニルエステル系単量体；ブタジエン、イソプレン、クロロプレンなどのジエン系単量体；ビニルグリシジルエーテル、アリルグリシジルエーテル、メタリルグリシジルエーテル、グリシジルアクリレート、グリシジルメタクリレートなどのグリシジル基含有単量体；およびこれら以外のオレフィン、不飽和エステル類、ハロゲン化オレフィン、ビニルエーテルなどが挙げられる。

【0052】重合性不飽和基含有単量体(C)は1種のみを使用してもよく2種以上を併用してもよい。シアノ基含有単量体、グリシジル基含有単量体またはスチレン系単量体を用いた場合、特にアクリロニトリル、グリシジルアクリレート、グリシジルメタクリレートまたはスチレンを用いた場合には、さらに優れた接着性や機械物性を発現しうるので好ましい。また、特に硬化後にゴム弾性を要する場合には、アクリル酸エステルを用いるのが好ましい。

【0053】重合性不飽和基含有単量体(C)として式(1)で表される加水分解性ケイ素基を有する重合性単量体を使用できる。このような加水分解性ケイ素基を有する重合性単量体としては特に下記式(7)で表される化合物が好ましい。



10

20

30

40

50

(式(7)中、 R^7 は重合性不飽和基を有する1価の有機基であり、 R^6 は炭素数1~20の置換または非置換の1価の有機基であり、Yは水酸基または加水分解性基であり、bは1、2または3である。ただし、 R^6 が複数個存在するときはそれらの R^6 は同じでも異なってもよく、Yが複数個存在するときはそれらのYは同じでも異なってもよい。)

【0054】加水分解性ケイ素基を有する重合性単量体としては、加水分解性ケイ素基を有するビニル単量体、加水分解性ケイ素基を有するアクリル単量体などが挙げられる。具体的には下記のもの挙げられ、3-アクリロイルオキシプロピルトリメトキシシラン、3-メタクリロイルオキシプロピルトリメトキシシランが特に好ましい。

【0055】ビニルメチルジメトキシシラン、ビニルメチルジエトキシシラン、ビニルメチルジクロロシラン、ビニルトリメトキシシラン、ビニルトリエトキシシラン、ビニルトリクロロシラン、トリス(2-メトキシエトキシ)ビニルシランなどのビニルシラン類、3-アクリロイルオキシプロピルメチルジメトキシシラン、3-メタクリロイルオキシプロピルメチルジメトキシシラン、3-アクリロイルオキシプロピルトリメトキシシラン、3-アクリロイルオキシプロピルトリエトキシシラン、3-メタクリロイルオキシプロピルトリメトキシシラン、3-メタクリロイルオキシプロピルトリエトキシシランなどのアクリロイルオキシシラン類、メタクリロイルオキシシラン類など。

【0056】これらの他にも、たとえばケイ素原子を2~30個有するポリシロキサン化合物であって炭素-炭素2重結合および加水分解性基と結合したケイ素原子を併有する化合物も加水分解性ケイ素基を有する重合性単量体として使用できる。

【0057】上記の加水分解性ケイ素基を有する重合性単量体は1種のみを使用してもよく、2種以上を併用してもよい。加水分解性ケイ素基を有する重合性単量体を用いる場合、この単量体は重合性不飽和基含有単量体(C)100重量部中、0.01~20重量部用いるのが好ましい。

【0058】重合性不飽和基含有単量体(C)の一部または全部は、重合性不飽和基を有し、かつ、グリシジル基および/または式(1)で表される加水分解性ケイ素基を有する単量体であることが好ましい。

【0059】(重合体組成物)ポリオキシアルキレン重合体(B)が、さらに重合体(D)を含有する場合、ポリオキシアルキレン重合体(B)と重合体(D)とからなる重合体組成物は、以下に示す(ト)~(ル)の方法で製造できる。

【0060】(ト)ポリオキシアルキレン重合体(B)とあらかじめ重合性不飽和基含有単量体(C)を重合して得られる重合体(D)を混合する方法。

(チ)ポリオキシアルキレン重合体(B)中において重合性不飽和基含有単量体(C)の重合を行う方法。

(リ)不飽和基を含有するポリオキシアルキレン重合体(F)中において重合性不飽和基含有単量体(C)の重合を行った後、重合体(F)中の残存する不飽和基を式(1)で表される加水分解性ケイ素基に変換する方法。変換方法は不飽和基に式(3)で表されるヒドロシリル化合物を反応させる方法が好ましい。

(ヌ)ポリオキシアルキレン重合体(B)の前駆体中において重合性不飽和基含有単量体(C)の重合を行った後、前駆体をポリオキシアルキレン重合体(B)に変換する方法。

(ル)溶剤または希釈剤の存在下で重合性不飽和基含有単量体(C)の重合を行った後、ポリオキシアルキレン重合体(B)と混合し、必要に応じて次いで溶剤または希釈剤を留去する方法。

【0061】溶剤は、重合性不飽和基含有単量体(C)の種類に応じて適宜選択しうる。希釈剤としては不飽和基含有ポリオキシアルキレン重合体(F)が好ましい。重合の際、溶剤または希釈剤中に不飽和基を含有するポリオキシアルキレン重合体(F)を存在させることもできる。

【0062】重合性不飽和基含有単量体(C)重合の際には、ラジカル発生剤などの重合開始剤を用いてもよく、場合によっては重合開始剤を用いることなく放射線や熱によって重合させてもよい。重合開始剤、重合温度、重合時間などについては、前記(二)で述べたのと同様である。

【0063】本発明において重合体(D)を用いる場合は、重量比でポリオキシアルキレン重合体(B)/重合体(D)が100/1~1/300となる範囲で使用されることが好ましい。100/1~1/100、さらに100/1~1/10の範囲で使用されるのが、作業性などの点で特に好ましい。

【0064】重合体(D)は、ポリオキシアルキレン重合体(B)中に、微粒子状に均一に分散していてもまた均一に溶解していてもよい。組成物の粘度や作業性を考慮した場合には微粒子状に均一に分散していることが好ましい。

【0065】本発明において重合体(A)とともに空気硬化性化合物(K)および/または光硬化性化合物

(L)を使用する。空気硬化性化合物(K)の使用は初期タックの改良に効果があり、光硬化性化合物(L)の使用は耐汚染性やクラック抑制の改良に効果がある。空気硬化性化合物(K)および光硬化性化合物(L)は併用することが特に好ましい。

【0066】本発明に使用される空気硬化性化合物(K)としては、空気中の酸素により重合を起こす不飽和基を分子内に有する化合物が好ましい。具体的には、乾性油、乾性油の変性物、液状ジエン系重合体または液

状ジエン系重合体の変性油が好ましい。

【0067】乾性油としては、桐油、アマニ油、エノ油、大豆油、ひまわり油、麻実油などが挙げられる。乾性油の変性物としては、乾性油を変性して得られる各種アルキッド樹脂、乾性油と官能性ポリオキシアルキレンとの反応生成物、乾性油とイソシアネート化合物との反応生成物（ウレタン化油）、乾性油により変性されたアクリル系重合体、乾性油により変性されたエポキシ樹脂、乾性油により変性されたシリコン樹脂が挙げられる。

【0068】液状ジエン系重合体およびその変性物としては、ブタジエン、クロロブレン、イソブレン、1, 3-ペンタジエンなどの炭素数4~8のジエン系化合物を単独重合または共重合させて得られる液状重合体、ジエン系化合物と共重合性を有するアクリロニトリル、スチレンなどの単量体をジエン系化合物が主体となるように共重合させて得られるNBR、SBRなどの重合体、それらの各種変性物（マレイン化変性物、ボイル油変性物など）が挙げられる。

【0069】これらのうちでは乾性油、液状ジエン系重合体および液状ジエン系重合体の変性物が好ましい。乾性油が特に好ましい。空気硬化性化合物（K）は1種単独で用いてもよく、2種以上を併用してもよい。

【0070】また、空気硬化性化合物（K）とともに酸化硬化反応を促進する触媒や金属ドライヤを併用すると効果が高められる場合がある。これらの触媒や金属ドライヤとしては、ナフテン酸コバルト、ナフテン酸鉛、ナフテン酸ジルコニウム、2-エチルヘキサン酸コバルト、2-エチルヘキサン酸ジルコニウムなどの金属塩や、アミン化合物などが挙げられる。

【0071】空気硬化性化合物（K）を使用する場合の使用量は重合体（A）または重合体（A）と重合体

（D）の合計100重量部に対して0.01~20重量部が好ましい。使用量が0.01重量部に満たないと空気硬化性化合物（K）の使用目的である初期タックの改善効果が不十分であり、20重量部を超えると硬化物の伸びなどが損なわれる。好ましい使用量は1~10重量部である。

【0072】本発明に使用される光硬化性化合物（L）とは光の作用によってかなり短時間に分子構造が化学変化をおこし硬化などの物性的変化を生ずるものである。この種の化合物としては単量体、オリゴマー、樹脂またはそれらを含む組成物など多くのものが知られており、市販されている任意のものを使用する。不飽和アクリル系化合物、ポリケイ皮酸ビニル類またはアジド化樹脂などが代表的なものであり、不飽和アクリル系化合物が特に好ましい。

【0073】不飽和アクリル系化合物としては、アクリロイル基またはメタクリロイル基を1~数個有する単量体、オリゴマー、またはそれらの混合物が好ましく、特

にアクリロイル基を有する化合物が好ましい。より具体的には多価アルコールのジ（メタ）アクリレートなどの単量体や該単量体を重合して得られる分子量10000以下のオリゴエステルが好ましい（（メタ）アクリレートとはアクリレートとメタクリレートを示す。以下同じ）。多価アルコールのジ（メタ）アクリレートの具体例としては、プロピレングリコールジ（メタ）アクリレート、ブチレングリコールジ（メタ）アクリレート、エチレングリコールジ（メタ）アクリレート、ネオペンチルグリコールジ（メタ）アクリレート、トリメチロールプロパントリ（メタ）アクリレート、などが挙げられる。

【0074】光硬化性化合物（L）を使用する場合の使用量は重合体（A）または重合体（A）と重合体（D）の合計100重量部に対して0.01~20重量部が好ましい。使用量が0.01重量部に満たないと光硬化性化合物（L）の使用目的である耐汚染性の改善が不十分であり、20重量部を超えると硬化物の伸びなどが損なわれる。好ましい使用量は1~10重量部である。

【0075】（室温硬化性組成物）本発明の室温硬化性組成物は、下記の添加剤を含むことも可能である。以下、添加剤について説明する。

【0076】（充填剤）充填剤としては公知の充填剤が使用できる。充填剤の使用量は重合体（A）または重合体（A）と重合体（D）の合計100重量部に対して0.001~1000重量部、特に50~250重量部が好ましい。充填剤の具体例としては以下のものが挙げられる。これらの充填剤は単独で用いてもよく、2種以上併用してもよい。

【0077】表面を脂肪酸または樹脂酸系有機物で表面処理した炭酸カルシウム、該炭酸カルシウムをさらに微粉末化した平均粒径1 μ m以下の膠質炭酸カルシウム、沈降法により製造した平均粒径1~3 μ mの軽質炭酸カルシウム、平均粒径1~20 μ mの重質炭酸カルシウムなどの炭酸カルシウム類、フュームドシリカ、沈降性シリカ、無水ケイ酸、含水ケイ酸およびカーボンブラック、炭酸マグネシウム、ケイソウ土、焼成クレー、クレー、タルク、酸化チタン、ベントナイト、有機ベントナイト、酸化第二鉄、酸化亜鉛、活性亜鉛華、シラスバルーン、ガラスバルーン、木粉、パルプ、木綿チップ、マイカ、くるみ殻粉、もみ殻粉、グラファイト、アルミニウム微粉末、フリント粉末などの粉体状充填剤。石綿、ガラス繊維、ガラスフィラメント、炭素繊維、ケブラー繊維、ポリエチレンファイバーなどの繊維状充填剤。

【0078】（可塑剤）可塑剤としては公知の可塑剤が使用できる。可塑剤の使用量は重合体（A）または重合体（A）と重合体（D）の合計100重量部に対して0.001~1000重量部が好ましい。可塑剤の具体例としては以下のものが挙げられる。

【0079】フタル酸ジオクチル、フタル酸ジブチル、

10

20

30

40

50

フタル酸ブチルベンジルなどのフタル酸エステル類。アジピン酸ジオクチル、コハク酸ビス(2-メチルノニル)、セバシン酸ジブチル、オレイン酸ブチルなどの脂肪族カルボン酸エステル。ペンタエリスリトールエステルなどのアルコールエステル類。リン酸トリオクチル、リン酸トリクレジルなどのリン酸エステル類。エポキシ化大豆油、4, 5-エポキシヘキサヒドロフタル酸ジオクチル、エポキシステアリン酸ベンジルなどのエポキシ可塑剤。塩素化パラフィン。2塩基酸と2価アルコールとを反応させてなるポリエステル類などのポリエステル系可塑剤。ポリオキシプロピレングリコールやその誘導体などのポリエーテル類、ポリ- α -メチルスチレン、ポリスチレンなどのスチレン系のオリゴマー類、ポリブタジエン、ブタジエン-アクリロニトリル共重合体、ポリクロロブレン、ポリイソブレン、ポリブテン、水添ポリブテン、エポキシ化ポリブタジエンなどのオリゴマー類などの高分子可塑剤。

【0080】(硬化促進触媒) 本発明における硬化性組成物を硬化させる際には加水分解性基含有ケイ素基の硬化反応を促進する硬化促進触媒を使用してもよい。具体的な例としては下記の化合物が挙げられる。それらの1種または2種以上が使用される。硬化促進触媒は重合体(A)または重合体(A)と重合体(D)の合計100重量部に対して0.001~10重量部使用することが好ましい。

【0081】アルキルチタン酸塩、有機ケイ素チタン酸塩、ビスマストリス-2-エチルヘキソエートなどの金属塩、リン酸、p-トルエンスルホン酸、フタル酸などの酸性化合物、ブチルアミン、ヘキシルアミン、オクチルアミン、デシルアミン、ラウリルアミンなどの脂肪族モノアミン、エチレンジアミン、ヘキサレンジアミンなどの脂肪族ジアミン、ジエチレントリアミン、トリエチレントトラミン、テトラエチレンペンタミンなどの脂肪族ポリアミン類、ピペリジン、ピペラジンなどの複素環式アミン類、メタフェニレンジアミンなどの芳香族アミン類、エタノールアミン類、トリエチルアミン、エポキシ樹脂の硬化剤として用いられる各種変性アミンなどのアミン化合物。2-エチルヘキサン酸スズ、ナフテン酸スズ、ステアリン酸スズなどの2価のスズ化合物と上記アミン類の混合物。

【0082】ジブチルスズジアセテート、ジブチルスズジラウレート、ジオクチルスズジラウレートおよび下記のカルボン酸型有機スズ化合物およびこれらのカルボン酸型有機スズ化合物と上記のアミン類との混合物。 $(n-C_4H_9)_2Sn(OCOCH=CHCOOCH_3)_2$ 、 $(n-C_4H_9)_2Sn(OCOCH=CHCOOC_4H_9-n)_2$ 、 $(n-C_8H_{17})_2Sn(OCOCH=CHCOOCH_3)_2$ 、 $(n-C_8H_{17})_2Sn(OCOCH=CHCOOC_4H_9-n)_2$ 、 $(n-C_8H_{17})_2Sn(OCOCH=CHCOOC_8H_{17}-iso)_2$ 。

【0083】下記の含硫黄型有機スズ化合物。 $(n-C_4H_9)_2Sn(SCH_2COO)$ 、 $(n-C_8H_{17})_2Sn(SCH_2COO)$ 、 $(n-C_8H_{17})_2Sn(SCH_2CH_2COO)$ 、 $(n-C_8H_{17})_2Sn(SCH_2COOCH_2CH_2OCOCH_2S)$ 、 $(n-C_4H_9)_2Sn(SCH_2COOC_8H_{17}-iso)_2$ 、 $(n-C_8H_{17})_2Sn(SCH_2COOC_8H_{17}-iso)_2$ 、 $(n-C_8H_{17})_2Sn(SCH_2COOC_8H_{17}-n)_2$ 、 $(n-C_4H_9)_2SnS$ 。

【0084】 $(n-C_4H_9)_2SnO$ 、 $(n-C_8H_{17})_2SnO$ などの有機スズオキシド、およびこれらの有機スズオキシドとエステル化合物との反応生成物。エステル化合物としてはエチルシリケート、マレイン酸ジメチル、マレイン酸ジエチル、マレイン酸ジオクチル、フタル酸ジメチル、フタル酸ジエチル、フタル酸ジオクチルなどが挙げられる。

【0085】下記などのキレートスズ化合物およびこれらのスズ化合物とアルコキシシランとの反応生成物(ただし、acacはアセチルアセトナト配位子を表す)。

$(n-C_4H_9)_2Sn(acac)_2$ 、 $(n-C_8H_{17})_2Sn(acac)_2$ 、 $(n-C_4H_9)_2(C_8H_{17}O)Sn(acac)$ 。

【0086】下記のスズ化合物。 $(n-C_4H_9)_2(CH_3COO)SnOSn(OCOCH_3)(C_4H_9-n)_2$ 、 $(n-C_4H_9)_2(CH_3O)SnOSn(OCH_3)(C_4H_9-n)_2$ 。

【0087】(接着性付与剤) さらに接着性を改良する目的で接着性付与剤が用いられる。これらの接着性付与剤としては(メタ)アクリロイルオキシ基含有シラン類、アミノ基含有シラン類、メルカプト基含有シラン類、エポキシ基含有シラン類、カルボキシル基含有シラン類などのシランカップリング剤が挙げられる。

【0088】(メタ)アクリロイルオキシ基含有シラン類としては、3-メタクリロイルオキシプロピルトリメトキシシラン、3-アクリロイルオキシプロピルトリメトキシシラン、3-メタクリロイルオキシプロピルメチルジメトキシシランなどが挙げられる。

【0089】アミノ基含有シラン類としては、3-アミノプロピルトリメトキシシラン、3-アミノプロピルメチルジメトキシシラン、N-(2-アミノエチル)-3-アミノプロピルトリメトキシシラン、N-(2-アミノエチル)-3-アミノプロピルメチルジメトキシシラン、N-(2-アミノエチル)-3-アミノプロピルトリエトキシシラン、3-ウレイドプロピルトリエトキシシラン、N-(N-ビニルベンジル-2-アミノエチル)-3-アミノプロピルトリメトキシシラン、3-アニリノプロピルトリメトキシシランなどが挙げられる。

【0090】メルカプト基含有シラン類としては、3-メルカプトプロピルトリメトキシシラン、3-メルカプト

トプロピルトリエトキシシラン、3-メルカプトプロピルメチルジメトキシシラン、3-メルカプトプロピルメチルジエトキシシランなどが挙げられる。

【0091】エポキシ基含有シラン類としては、3-グリシジルオキシプロピルトリメトキシシラン、3-グリシジルオキシプロピルメチルジメトキシシラン、3-グリシジルオキシプロピルトリエトキシシランなどが挙げられる。

【0092】カルボキシル基含有シラン類としては、2-カルボキシエチルトリエトキシシラン、2-カルボキシエチルフェニルビス(2-メトキシエトキシ)シラン、N-(N-カルボキシルメチル-2-アミノエチル)-3-アミノプロピルトリメトキシシランなどが挙げられる。

【0093】また2種以上のシランカップリング剤を反応させて得られる反応物を用いてもよい。反応物の例としてはアミノ基含有シラン類とエポキシ基含有シラン類との反応物、アミノ基含有シラン類と(メタ)アクリロイルオキシ基含有シラン類との反応物、エポキシ基含有シラン類とメルカプト基含有シラン類の反応物、メルカプト基含有シラン類どうしの反応物などが挙げられる。これらの反応物は該シランカップリング剤を混合し室温～150℃の温度範囲で1～8時間攪拌することによって容易に得られる。

【0094】上記の化合物は単独で使用してもよく、2種類以上併用してもよい。シランカップリング剤の使用量は重合体(A)、または重合体(A)と重合体(D)の合計100重量部に対して0～30重量部が好ましい。

【0095】接着性付与剤として、エポキシ樹脂を添加してもよい。また必要に応じてさらにエポキシ樹脂硬化剤を併用してもよい。本発明の組成物に添加しうるエポキシ樹脂としては、一般のエポキシ樹脂が挙げられる。具体的には以下のものが例示できる。使用量は重合体(A)、または重合体(A)と重合体(D)の合計100重量部に対して0～100重量部が好ましい。

【0096】ビスフェノールA-ジグリシジルエーテル型エポキシ樹脂、ビスフェノールF-ジグリシジルエーテル型エポキシ樹脂、テトラプロモビスフェノールA-ジグリシジルエーテル型エポキシ樹脂などの難燃型エポキシ樹脂、ノボラック型エポキシ樹脂、水添ビスフェノールA型エポキシ樹脂、ビスフェノールA-プロピレンオキシド付加物のグリシジルエーテル型エポキシ樹脂、4-グリシジルオキシ安息香酸グリシジル、フタル酸ジグリシジル、テトラヒドロフタル酸ジグリシジル、ヘキサヒドロフタル酸ジグリシジルなどのジグリシジルエステル系エポキシ樹脂、m-アミノフェノール系エポキシ樹脂、ジアミノジフェニルメタン系エポキシ樹脂、ウレタン変性エポキシ樹脂、各種脂環式エポキシ樹脂、N,N-ジグリシジルアニリン、N,N-ジグリシジルーo-

トルイジン、トリグリシジルイソシアヌレート、ポリアルキレングリコールジグリシジルエーテル、グリセリンなどの多価アルコールのグリシジルエーテル、ヒダントイン型エポキシ樹脂、石油樹脂などの不飽和重合体のエポキシ化物などの一般に使用されているエポキシ樹脂やエポキシ基を含有するビニル系重合体など。

【0097】また本発明の組成物に上記エポキシ樹脂の硬化剤(または硬化触媒)を併用してもよい。このような硬化剤としては一般に用いられるエポキシ樹脂用硬化剤が挙げられる。具体的には以下のものが例示できる。使用量はエポキシ樹脂に対して0.1～300重量部が好ましい。

【0098】トリエチレンテトラミン、テトラエチレンペンタミン、ジエチルアミノプロピルアミン、N-アミノエチルピペラジン、m-キシリレンジアミン、m-フェニレンジアミン、ジアミノジフェニルメタン、ジアミノジフェニルスルホン、イソホロンジアミン、2,4,6-トリス(ジメチルアミノメチル)フェノールなどのアミン類またはそれらの塩類、またはケチミン化合物などのブロックドアミン類、ポリアミド樹脂、イミダゾール類、ジシアンジアミド類、三フッ化ホウ素錯化合物類、無水フタル酸、ヘキサヒドロフタル酸無水物、テトラヒドロフタル酸無水物、ドデセニルコハク酸無水物、ピロメリット酸無水物などのカルボン酸無水物、フェノキシ樹脂、カルボン酸類、アルコール類、エポキシ基と反応しうる基を平均して分子内に少なくとも1個有するポリアルキレンオキシド系重合体(末端アミノ化ポリオキシプロピレングリコール、末端カルボキシル化ポリオキシプロピレングリコールなど)、末端が水酸基、カルボキシル基、アミノ基などで修飾されたポリブタジエン、水添ポリブタジエン、アクリロニトリル-ブタジエン共重合体、アクリル系重合体などの液状末端官能基含有重合体など。

【0099】(溶剤)また本発明の組成物を硬化性組成物として用いる場合、粘度の調整、組成物の保存安定性向上を目的として、溶剤を添加することもできる。溶剤の使用量は重合体(A)、または重合体(A)と重合体(D)の合計100重量部に対して0.001～500重量部が好ましい。

【0100】溶剤としては脂肪族炭化水素類、芳香族炭化水素類、ハロゲン化炭化水素類、アルコール類、ケトン類、エステル類、エーテル類、エステルアルコール類、ケトンアルコール類、エーテルアルコール類、ケトンエーテル類、ケトンエステル類、エステルエーテル類を使用できる。アルコール類は、本発明の組成物を長期に保存する場合、保存安定性が向上するので好ましい。アルコール類としては、炭素数1～10のアルキルアルコールが好ましく、メタノール、エタノール、イソプロパノール、イソペンチルアルコール、ヘキシルアルコールなどが特に好ましい。

【0101】(脱水剤) また本発明の硬化性組成物の貯蔵安定性をさらに改良するために、硬化性や柔軟性に悪影響を及ぼさない範囲で少量の脱水剤を添加できる。脱水剤の使用量は重合体(A)、または重合体(A)と重合体(D)の合計100重量部に対して0.001~30重量部が好ましい。

【0102】具体的には、オルトギ酸メチル、オルトギ酸エチルなどのオルトギ酸アルキル、オルト酢酸メチル、オルト酢酸エチルなどのオルト酢酸アルキル、メチルトリメトキシシラン、ビニルトリメトキシシラン、テトラメトキシシラン、テトラエトキシシランなどの加水分解性有機シリコン化合物、加水分解性有機チタン化合物などを使用しうる。ビニルトリメトキシシラン、テトラエトキシシランがコスト、効果の点から特に好ましい。

【0103】(チキソ性付与剤) また垂れ性の改善のためチキソ性付与剤を使用してもよい。このようなチキソ性付与剤としては水添ひまし油、脂肪酸アミドなどが用いられる。

【0104】(老化防止剤) また、老化防止剤としては、一般に用いられている酸化防止剤、紫外線吸収剤、光安定剤が適宜用いられる。ヒンダードアミン系、ベンゾトリアゾール系、ベンゾフェノン系、ベンゾエート系、シアノアクリレート系、アクリレート系、ヒンダードフェノール系、リン系、硫黄系の各化合物を適宜使用できる。

【0105】(その他) 顔料として、酸化鉄、酸化クロム、酸化チタンなどの無機顔料およびフタロシアニンブルー、フタロシアニングリーンなどの有機顔料が挙げられる。

【0106】本発明の室温硬化性組成物は、シーラント、防水材、接着剤、コーティング剤などに使用でき、特に硬化物自体の十分な凝集力と被着体への動的追従性が要求される用途に好適である。

【0107】

【実施例】製造例1~23で製造した重合体(P1~P23)を用いて、硬化物を作製した実施例および比較例を以下に示す。なお、部とは重量部を示す。製造例1~13において、水酸基価換算分子量とは、原料である水酸基を有するポリオキシアルキレン重合体の水酸基価から換算した分子量を示す。 M_w/M_n はゲルパーミエーションクロマトグラフにより溶媒としてテトラヒドロフランを用いて測定した値である。検量線はポリオキシアルキレンポリオールを用いて作成した。製造例14~17においては、分子量はゲルパーミエーションクロマトグラフにより溶媒としてテトラヒドロフランを用いて測定した。検量線はポリスチレンを用いて作成した。

【0108】(製造例1) グリセリンを開始剤とし亜鉛ヘキサシアノコバルテート-グライム錯体触媒の存在下プロピレンオキシドを反応させた。水酸基価換算分子量

17000、かつ $M_w/M_n=1.3$ のポリプロピレンオキシドにナトリウムメトキシドのメタノール溶液を添加し、加熱減圧下メタノールを留去してポリプロピレンオキシドの末端水酸基をナトリウムアルコキシドに変換した。次に塩化アリルを反応させた。未反応の塩化アリルを除去し、精製して、アリル基末端ポリプロピレンオキシドを得た(これを重合体U1とする。)。残存する水酸基を水酸基価の測定法で分析したところ0.01ミリモル/gであった。重合体U1に対しヒドロシリル化合物であるトリメトキシシランを白金触媒の存在下反応させ、末端に平均2個のトリメトキシシリル基を有する重合体P1を得た。

【0109】(製造例2) プロピレングリコールを開始剤とし亜鉛ヘキサシアノコバルテート-グライム錯体触媒の存在下プロピレンオキシドを反応させて得られた水酸基価換算分子量17000、かつ $M_w/M_n=1.3$ のポリプロピレンオキシドを用い、製造例1と同様の方法で末端にアリル基を有するポリプロピレンオキシドを得た(残存する水酸基は0.01ミリモル/g)。この反応物に対しヒドロシリル化合物であるトリメトキシシランを白金触媒の存在下反応させ、末端に平均1.3個のトリメトキシシリル基を有する重合体P2を得た。

【0110】(製造例3) ソルビトールを開始剤とし亜鉛ヘキサシアノコバルテート-グライム錯体触媒の存在下プロピレンオキシドを反応させて得られた水酸基価換算分子量15000、かつ $M_w/M_n=1.3$ のポリプロピレンオキシドを用い、製造例1と同様の方法で末端にアリル基を有するポリプロピレンオキシドを得た(残存する水酸基は0.01ミリモル/g)。この反応物に対しヒドロシリル化合物であるトリメトキシシランを白金触媒の存在下反応させ、末端に平均3.9個のトリメトキシシリル基を有する重合体P3を得た。

【0111】(製造例4) 製造例1で製造した重合体U1に対し、ヒドロシリル化合物であるメチルジメトキシシランとトリメトキシシランとをモル比にして30対70の割合に混合した混合物を白金触媒の存在下反応させ、末端に平均0.6個のメチルジメトキシシリル基と平均1.4個のトリメトキシシリル基を併有する重合体P4を得た。

【0112】(製造例5) 製造例1で製造した重合体U1に対し、シリル化合物である3-メルカプトプロピルトリメトキシシランを、重合開始剤である2,2'-アゾビス-2-メチルプロピロニトリルを用いて反応させ、末端に平均2個のトリメトキシシリル基を有する重合体P5を得た。

【0113】(製造例6) グリセリンを開始剤として亜鉛ヘキサシアノコバルテート触媒を用いてプロピレンオキシドの重合を行い、水酸基価換算分子量17000、かつ $M_w/M_n=1.3$ のポリオキシプロピレントリオールを得た後、精製した。これにイソシアネートプロピ

ルトリメトキシシランを加え、ウレタン化反応を行い両末端をトリメトキシシリル基に変換して、末端に平均2個のトリメトキシシリル基を有する分子量18000の重合体P6を得た。

【0114】（製造例7）製造例1で製造した重合体U1に対し、ヒドロシリル化合物であるメチルジメトキシシランを白金触媒の存在下反応させ、末端に平均2個のメチルジメトキシシリル基を有する重合体P7を得た。

【0115】（製造例8）製造例7においてヒドロシリル化合物としてメチルジメトキシシランの代わりにメチルジエトキシシランを使用する以外は製造例7と同様に行い、重合体P7の代わりに末端に平均2個のメチルジエトキシシリル基を有する重合体P8を得た。

【0116】（製造例9）プロピレングリコールを開始剤とし亜鉛ヘキサシアノコバルテートグライム錯体触媒の存在下プロピレンオキシドを反応させて得られた水酸基価換算分子量7000、かつ $M_w/M_n=1.2$ のポリプロピレンオキシドを用い、製造例1と同様の方法で末端にアシル基を有するポリプロピレンオキシドを得た（残存する水酸基は0.01ミリモル/g）。この反応物に対しヒドロシリル化合物であるメチルジメトキシシランを白金触媒の存在下反応させ、末端に平均1.3個のメチルジメトキシシリル基を有する重合体P9を得た。

【0117】（製造例10）プロピレングリコールを開始剤とし亜鉛ヘキサシアノコバルテートグライム錯体触媒の存在下プロピレンオキシドを反応させて得られた水酸基価換算分子量7000、かつ $M_w/M_n=1.2$ のポリプロピレンオキシドを用い、製造例1と同様の方法で末端にアシル基を有するポリプロピレンオキシドを得た（残存する水酸基は0.01ミリモル/g）。この反応物に対しヒドロシリル化合物であるトリメトキシシランを白金触媒の存在下反応させ、末端に平均1.3個のトリメトキシシリル基を有する重合体P10を得た。

【0118】（製造例11）水酸化カリウム触媒を用いて得られた水酸基価換算分子量3000のポリオキシプロピレンジオールにナトリウムメトキシドのメタノール溶液を添加し、加熱減圧下メタノールを留去して末端水酸基をナトリウムアルコキシドに変換した。次にクロロプロモタンと反応させて高分子量化を行った後、続いて塩化アシルを反応させた。未反応の塩化アシルを除去し、精製して、末端にアシルオキシ基を有するポリプロピレンオキシド（ $M_w/M_n=1.9$ ）を得た（残存する水酸基は0.01ミリモル/g）。これにヒドロシリル化合物であるトリメトキシシランを白金触媒の存在下に反応させて末端に平均1.3個のトリメトキシシリル基を有する分子量7000の重合体P11を得た。

【0119】（製造例12）水酸化カリウム触媒を用いて得られた水酸基価換算分子量6000、かつ $M_w/M_n=1.9$ のポリオキシプロピレンジオールを用い、製

造例1と同様の方法で末端にアシルオキシ基を有するポリプロピレンオキシドを得た（残存する水酸基は0.01ミリモル/g）。これにヒドロシリル化合物であるトリメトキシシランを白金触媒の存在下に反応させて、末端に平均1.3個のトリメトキシシリル基を有する重合体P12を得た。

【0120】（製造例13）製造例1で製造した重合体U1に対し、ヒドロシリル化合物であるトリエトキシシランを白金触媒の存在下反応させ、末端に平均2個のトリエトキシシリル基を有する重合体P13を得た。

【0121】（実施例1～20および比較例1～4）重合体P1～P13のうち、表1～3に示す重合体100部に対し、脂肪酸表面処理炭酸カルシウム100部、重質炭酸カルシウム50部、表1～3に示す可塑剤を50部または0部、チキソ性付与剤3部、表1～3に示す紫外線吸収剤、ヒンダードアミン系光安定剤および酸化防止剤を各1部、空気硬化性化合物5部、表1～3に示す光硬化性化合物3部、硬化触媒として2-エチルヘキサンスズ2部とラウリルアミン0.7部をあらかじめ混合したもの、またはジブチルスズビスアセチルアセトナート2部を添加して、均一に混合し硬化性組成物を得た。

【0122】この組成物の内部硬化性評価のため、組成物粘度が20℃65%湿度条件下で160万cpsに到達する時間を測定した。また混練した組成物を20℃、65%湿度下に7日、50℃、60%湿度下に7日養生して厚さ5mmのシートを得た。このシートの250時間後、500時間後および750時間後の表面耐候性をサンシャインウェザオメータで調べた。評価は、サンシャインウェザオメータ試験後に表面クラックが認められないものを○、ヘアクラックが認められるものを△、明らかにクラックが認められるものを×とした。結果を表1～表3に示す。

【0123】（重合体の末端基）

TM：トリメチルシリル基、DM：メチルジメトキシシリル基、TE：トリエトキシシリル基、DE：メチルジメトキシシリル基。

【0124】（空気硬化性化合物）

A：桐油、B：重合桐油（支那桐4号）、C：ウレタン化油（UO-5）、D：アマニ油変成アルキッド（HL-20）（A～D：トーメンケミカル社品）、E：液状ポリブタジエンR-15HT（出光石油化学（株）製）。

【0125】（光硬化性化合物）

A：アロニクスM309、B：M400、C：M8060（A～C：東亜合成（株）製）、D：KAYARAD（日本化薬（株）製）、E：アクリル酸フルオロアルキル（ $C_8F_{17}C_2H_4$ ）エステル、F：アクリル酸フルオロアルキル（ $C_8F_{17}C_3H_6$ ）エステル（E、F：旭硝子（株）製）。

【0126】（紫外線吸収剤）

A:チヌビン3277、B:チヌビン213(A、B:チバ・スペシャリティーケミカルズ品)。

【0127】(ヒンダードアミン系光安定剤)

A:アデカスタブLA-52、B:アデカスタブLA-62、C:アデカスタブLA-67、D:アデカスタブLA63P(A~D:旭電化工業(株)製)、E:チヌビン144、F:チヌビン765、G:CHIMASS OPB119FL(E~G:チバ・スペシャリティーケミカルズ製)、H:サノールLS765(H:三共(株)製)。

【0128】(酸化防止剤)

A:スチレン化フェノール(ノクラックSP、大内新興化学)、B:2,6-ジ-tert-ブチル-4-メチルフェノール、C:イルガノックス245(B、C:チバ・スペシャリティーケミカルズ製)。

【0129】(可塑剤)

A:フタル酸ジ(2-エチルヘキシル)、B:分子量10000のポリオキシプロピレングリコール末端アリエーテル、C:4,5-エポキシシクロヘキサンジカルボン酸ジ(2-エチルヘキシル)。

【0130】(硬化触媒)

A:オクチル酸スズとラウリルアミンの混合物、B:ジブチルスズビスアセチルアセトナート。

【0131】(製造例14)特開平1-170681に記載された方法に基づき1,4-ビス(1-クロロ-1-メチルエチル)ベンゼンを開始剤として三塩化ホウ素を触媒としてイソブチレンを重合させた後脱塩化水素して製造した両末端に約92%の割合でイソプロペニル基を有する分子量が約5000のイソブチレン系重合体に塩化白金酸を触媒としてトリクロロシランを90℃12時間(30)で反応させ、さらにオルトギ酸メチルとメタノールを反応させることで末端に平均1.2個のトリメトキシシリル基を有するポリイソブチレン系重合体P14を得た。

【0132】(製造例15)特開平1-170681に記載された方法に基づき1,4-ビス(1-クロロ-1-メチルエチル)ベンゼンを開始剤として三塩化ホウ素を触媒としてイソブチレンを重合させた後脱塩化水素して製造した両末端に約92%の割合でイソプロペニル基を有する分子量が約5000のイソブチレン系重合体に塩化白金酸を触媒としてメチルジクロロシランを90℃12時間(40)で反応させ、さらにオルトギ酸メチルとメタノールを反応させることで末端に平均1.2個のメチルジメトキシシリル基を有するポリイソブチレン系重合体P15を得た。

【0133】(製造例16)末端に水酸基を有する水添ポリブタジエン(ポリテールHA、三菱化学(株)製)の末端水酸基に対して90モル%の3-イソシアネートプロピルトリメトキシシランを反応させて、末端に平均1.3個のトリメトキシシリル基を有する水添ポリブタ

ジエン重合体P16を得た。

【0134】(製造例17)末端に水酸基を有する水添ポリブタジエン(ポリテールHA、三菱化学(株)製)の末端水酸基に対して90モル%の3-イソシアネートプロピルメチルジメトキシシランを反応させて、末端に平均1.3個のメチルジメトキシシリル基を有する水添ポリブタジエン重合体P17を得た。

【0135】(実施例21~27および比較例5~7)重合体P14~P17のうち、表4、5に示す重合体100部に対し、膠質炭酸カルシウム100部、重質炭酸カルシウム40部、炭化水素系高沸点溶剤(日本石油化学工業(株)ハイゾール)65部、硫酸ナトリウム水和物5部、タレ止め剤1部、空気硬化性化合物5部、光硬化性化合物3部、紫外線吸収剤1部、ヒンダードアミン系光安定剤1部、酸化防止剤1部を添加して、さらに、オクチル酸スズ2部とラウリルアミン0.7部の混合物またはジブチルスズビスアセチルアセトナート2部を混合して硬化性組成物とした。

【0136】この組成物について実施例1~20と同様の試験を行った。結果を表4、5に示す。

【0137】(製造例18)重合体P1の100gを攪拌機つきの反応器に入れて100℃に加熱し、そこへ滴下ロートから、アクリロニトリル15gとスチレン15gおよび2,2'-アゾビスイソブチロニトリル0.3gの溶液を攪拌しながら3時間かけて添加した。さらに2時間100℃で加熱攪拌を続けてから、減圧下に脱気操作を行い、白濁状の重合体混合物P18を得た。

【0138】(製造例20)重合体P1の50gおよび重合体P7の50gを攪拌機つきの反応器にいれ、トルエン50gを加えて希釈した。この混合物を100℃に加熱し、アクリロニトリル20g、スチレン20g、グリシジルメタクリレート5g、および3-メタクリロイルオキシプロピルトリメトキシシラン2gに2,2'-アゾビスイソブチロニトリル0.3gを溶解した溶液を3時間かけて攪拌下滴下した。滴下終了後さらに2,2'-アゾビスイソブチロニトリル0.2gのトルエン溶液を30分かけて滴下した後、100℃で3時間加熱攪拌した。得られた混合物から100℃減圧下でトルエンを留去して、白濁状の重合体混合物P20を得た。

【0139】(製造例22)重合体P13の100gを攪拌機つきの反応器にいれた。これを100℃に加熱し、スチレン5g、メタクリル酸メチル10g、メタクリル酸ブチル7g、メタクリル酸オクタデシル2g、3-メタクリロイルオキシプロピルトリメトキシシラン18g、2,2'-アゾビスイソブチロニトリル0.5gを溶解した溶液を3時間かけて攪拌下滴下した。滴下終了後さらに2,2'-アゾビスイソブチロニトリル0.2gのトルエン溶液を30分かけて滴下した後、100℃で3時間加熱攪拌した。得られた混合物から100℃減圧下でトルエンを留去して、白濁状の重合体混合物P

22を得た。

【0140】（製造例23）原料を重合体P13に代えて重合体P8（メチルジエトキシシリル基末端）を使用すること以外は、製造例22と同様にして重合体P23を製造した。

【0141】（実施例28～34および比較例8～10）重合体P18～P23のうち、表6、7に示す重合体100部に対し、膠質炭酸カルシウム100部、重質炭酸カルシウム40部、可塑剤30部または0部、硫酸ナトリウム水和物5部、タレ止め剤1部、空気硬化性化*10

* 合物5部、光硬化性化合物3部、紫外線吸収剤1部、ヒンダードアミン系光安定剤1部、酸化防止剤1部を添加し、さらに、オクチル酸スズ2部とラウリルアミン0.7部の混合物またはジブチルスズビスアセチルアセトナート2部を混合して硬化性組成物とした。この組成物について実施例1～20と同様の試験を行った。結果を表6、7に示す。

【0142】

【表1】

	実施例1	実施例2	実施例3	実施例4	実施例5	実施例6	実施例7	実施例8	実施例9
重合体	P1	P1	P1	P1	P1	P1	P1	P1	P2
重合体末端基	TM	TM	TM	TM	TM	TM	TM	TM	TM
空気硬化性化合物	A	B	C	D	E	A	A	A	A
光硬化性化合物	A	A	B	B	C	D	A+E (1:1)	A+F (1:1)	A
紫外線吸収剤	A	A	A	A	B	B	B	B	A
光安定剤	B	A	C	D	E	F	G	H	B
酸化防止剤	C	A	B	A	A	B	C	C	A
可塑剤	A+C (1:1)	A+C (1:1)	A+C (1:1)	A+C (1:1)	A+C (1:1)	A	A+C (1:1)	B	A+C (1:1)
硬化触媒	A	A	A	A	A	B	A	B	A
160万cps達成時間(h)	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
表面	250 hr	○	○	○	○	○	○	○	○
耐候	500 hr	○	○	○	○	○	○	○	○
性	750 hr	○	○	○	○	○	○	○	○

【0143】

【表2】

	実施 例 10	実施 例 11	実施 例 12	実施 例 13	実施 例 14	実施 例 15	実施 例 16	実施 例 17	実施 例 18
重合体	P 3	P 4	P 5	P 6	P10	P11	P12	P13	P 1
重合体末端基	TM	TM/DM	TM	TM	TM	TM	TM	TE	TM
空気硬化性 化合物	A	A	A	B	B	B	B	B	A
光硬化性 化合物	A	A	A	A	A	A	A	A	A+F (1:1)
紫外線吸収剤	A	A	A	A	A	A	A	A	B
光安定剤	B	B	D	D	D	E	E	E	H
酸化防止剤	A	B	B	C	C	C	C	C	C
可塑剤	C (1:1)	C (1:1)	A+C (1:1)	A	A	B	B	B	なし
硬化触媒	A	A	A	B	B	B	B	B	B
160万cps達成 時間(h)	0.5	1	0.5	0.5	0.5	1.5	1.5	1	0.5
表面 耐候 性	250 hr	○	○	○	○	○	○	○	○
	500 hr	○	○	○	○	○	○	○	○
	750 hr	○	○	○	○	○	○	○	○

【0144】

* * 【表3】

	実施 例 19	実施 例 20	比較 例 1	比較 例 2	比較 例 3	比較 例 4
重合体	P 1	P 1	P 7	P 8	P 9	P 1
重合体末端基	TM	TM	DM	DE	DM	TM
空気硬化性化合物	なし	A	A	B	B	なし
光硬化性化合物	A	なし	A	A	A	なし
紫外線吸収剤	A	A	A	A	A	A
光安定剤	B	B	B	E	D	B
酸化防止剤	C	C	C	C	C	C
可塑剤	A+C (1:1)	A+C (1:1)	A+C (1:1)	B	A	A+C (1:1)
硬化触媒	A	A	A	B	B	A
160万cps達成時間 (h)	0.5	0.5	4	8	7	0.5
表面 耐候性	250 hr	○	○	○	○	△
	500 hr	○	○	○	○	△
	750 hr	△	△	○	○	△~×

【0145】

【表4】

	実施 例 21	実施 例 22	実施 例 23	実施 例 24	実施 例 25
重合体	P14	P14	P16	P14/P15 (1:1)	P14/P15 (1:1)
重合体末端基	TM	TM	TM	TM/DM	TM/DM
空気硬化性化合物	A	A	A	A	A
光硬化性化合物	A	A	A	A	A
紫外線吸収剤	A	A	A	A	A
光安定剤	B	B	B	B	B
酸化防止剤	C	C	C	C	C
硬化触媒	A	B	A	A	B
160万cps達成時間 (h)	1	0.5	1	2	1.5
表面 耐候 性	1000 hr	○	○	○	○
	2000 hr	○	○	○	○
	3000 hr	○	○	○	○

【0146】

* * 【表5】

	実施 例 26	実施 例 27	比較 例 5	比較 例 6	比較 例 7
重合体	P14	P14	P15	P17	P14
重合体末端基	TM	TM	DM	DM	TM
空気硬化性化合物	なし	A	A	A	なし
光硬化性化合物	A	なし	A	A	なし
紫外線吸収剤	A	A	A	A	A
光安定剤	B	B	B	B	B
酸化防止剤	C	C	C	C	C
硬化触媒	A	B	A	A	A
160万cps達成時間 (h)	1	0.5	4.5	5	1
表面 耐候 性	1000 hr	○	○	○	△
	2000 hr	○~△	○	○	△
	3000 hr	△	△	○	×

【0147】

【表6】

	実施 例 28	実施 例 29	実施 例 30	実施 例 31	実施 例 32
重合体	P18	P18	P18	P20	P22
重合体末端基	TM	TM	TM	TM/DM	TE
空気硬化性化合物	A	B	B	A	B
光硬化性化合物	A	A	A	B	A
紫外線吸収剤	A	A	A	A	A
光安定剤	B	A	A	C	E
酸化防止剤	C	A	A	B	C
可塑剤	A+C (1:1)	B	なし	A+C (1:1)	B
硬化触媒	A	B	B	A	B
160万cps達成時間 (h)	0.5	0.5	0.5	0.5	0.5
表面耐 候性	250 hr	○	○	○	○
	500 hr	○	○	○	○
	750 hr	○	○	○	○

*【0148】
【表7】

10

20

*

	実施 例 33	実施 例 34	比較 例 8	比較 例 9	比較 例 10
重合体	P18	P18	P21	P23	P18
重合体末端基	TM	TM	DM	DE	TM
空気硬化性化合物	なし	A	A	B	なし
光硬化性化合物	A	なし	B	A	なし
紫外線吸収剤	A	A	A	A	A
光安定剤	B	B	C	E	B
酸化防止剤	C	C	B	C	C
可塑剤	A+C (1:1)	A+C (1:1)	A+C (1:1)	B	A+C (1:1)
硬化触媒	A	A	A	B	A
160万cps達成時間 (h)	0.5	0.5	3	4.5	0.5
表面耐 候性	250 hr	○	○	○	△
	500 hr	△	○	○	○~△
	750 hr	△	△	○	△~×

【0149】

【発明の効果】本発明の室温硬化性組成物はきわめて硬

化性および表面耐候性に優れるという効果を有する。

フロントページの続き

(72)発明者 林 朋美
神奈川県横浜市神奈川区羽沢町1150番地
旭硝子株式会社内

Fターム(参考) 4J002 AC072 AC082 AE052 BB201
BC031 BF011 BF021 BG011
BG041 BG051 BG061 BG072
BG101 BL001 BL012 BL022
BQ001 CD162 CD191 CD202
CF171 CG021 CH051 CH052
CK022 CP032 CP131 CP181
EG046 EG076 EH070 EN006
FD010 FD020 FD030 FD090
FD150 FD156 FD340 GH00
GJ01 GJ02